

UNIVERSITY OF ILLINOIS BULLETIN

Vol. VI.

DECEMBER 22, 1908

No. 18

[Entered Feb. 14, 1902, at Urbana, Ill., as second-class matter under Act of Congress July 16, 1894]

---

CIRCULAR NO. 3

FUEL TESTS WITH ILLINOIS COAL

(COMPILED FROM TESTS MADE BY THE TECHNOLOGIC BRANCH OF THE  
UNITED STATES GEOLOGICAL SURVEY, AT THE ST. LOUIS FUEL  
TESTING PLANT, 1904—JUNE 30, 1907).

BY

L. P. BRECKENRIDGE

AND

PAUL DISERENS



UNIVERSITY OF ILLINOIS  
ENGINEERING EXPERIMENT STATION

---

URBANA, ILLINOIS  
PUBLISHED BY THE UNIVERSITY



THE Engineering Experiment Station was established by action of the Board of Trustees, December 8, 1903. It is the purpose of the Station to carry on investigations along various lines of engineering and to study problems of importance to professional engineers and to the manufacturing, railway, mining, constructional, and industrial interests of the State.

The control of the Engineering Experiment Station is vested in the heads of the several departments of the College of Engineering. These constitute the Station Staff, and with the Director, determine the character of the investigations to be undertaken. The work is carried on under the supervision of the Staff; sometimes by a research fellow as graduate work, sometimes by a member of the instructional force of the College of Engineering, but more frequently by an investigator belonging to the Station corps.

The results of these investigations are published in the form of bulletins, which record mostly the experiments of the Station's own staff of investigators. There will also be issued from time to time in the form of circulars, compilations giving the results of the experiments of engineers, industrial works, technical institutions, and governmental testing departments.

The volume and number at the top of the title page of the cover are merely arbitrary numbers and refer to the general publications of the University of Illinois; *above the title is given the number of the Engineering Experiment Station bulletin or circular, which should be used in referring to these publications.*

For copies of bulletins, circulars or other information address the Engineering Experiment Station, Urbana, Illinois.

UNIVERSITY OF ILLINOIS  
ENGINEERING EXPERIMENT STATION

---

CIRCULAR NO. 3

DECEMBER 1908

---

FUEL TESTS WITH ILLINOIS COAL

(COMPILED FROM TESTS MADE BY THE TECHNOLOGIC BRANCH OF THE  
UNITED STATES GEOLOGICAL SURVEY, AT THE ST. LOUIS, MO., FUEL  
TESTING PLANT, 1904-JUNE 30, 1907.)

BY

L. P. BRECKENRIDGE, DIRECTOR OF THE ENGINEERING EXPERIMENT STATION,  
ALSO CONSULTING ENGINEER, TECHNOLOGIC BRANCH, U. S. G. S.

AND

PAUL DISERENS, M. E.

CONTENTS

	Page
I. Introduction . . . . .	2
II. A Summary of Conclusions . . . . .	2
III. The Coals Tested . . . . .	4
IV. Chemical Properties of the Coals Tested . . . . .	9
V. Washing Tests . . . . .	18
VI. Coking Tests . . . . .	23
VII. Steaming Tests . . . . .	26
VIII. Producer-Gas Tests . . . . .	43

## I INTRODUCTION

The United States Geological Survey Technologic Branch has conducted at the St. Louis, Missouri, fuel testing plant, a series of investigations on the fuels of the United States. These tests included a large number of Illinois coals. The results of the tests have been published from time to time in a series of government bulletins which contain very full descriptions of methods and very complete details of the results obtained. A complete list of the government bulletins is given at the end of this publication.

The tests included:

- (a) Steaming tests under boilers
- (b) Producer-gas tests
- (c) Washing tests
- (d) Coking tests
- (e) Briquetting tests
- (f) Chemical tests for composition and heating values
- (g) Field work tests, sampling tests and a few other minor investigations.

It is the purpose of this circular to present in compact form the important results of the government tests so far as these tests relate to Illinois coals. The Engineering Experiment Station hopes that by bringing together in one circular the tests made by the government on Illinois coals, it may do a service to the engineering, industrial and fuel interests of the State. The compiler has presented a few conclusions which seem justified by a study of the results recorded from tests already made. It is, however, fair to say that in a few cases the number of tests made is scarcely sufficient to warrant any general application of the conclusions stated.

## II A SUMMARY OF CONCLUSIONS

The results of the United States Geological Survey tests of Illinois coal, presented in the following pages, seem to justify the conclusions given below.

1. The chemical properties of the coals tested indicate that



on a basis of the volatile-carbon total-carbon ratio ( $\frac{VC}{C}$ ), all Illinois coals tested belong in Class B or Class D\*. The maximum value of this ratio is 33.4 per cent and the minimum value is 20.9 per cent.

2. The average calorific value of Illinois coal is 14319 B. t. u. per pound of pure coal (ash and moisture free). But few samples tested varied from this value by an amount more than 2 per cent.

3. The quality of Illinois coal is greatly increased by washing. The reduction in ash and in sulphur is as follows:—

When raw coal contains 8% ash, the reduction in ash is 20%.

When raw coal contains 12% ash, the reduction in ash is 30%.

When raw coal contains 16% ash, the reduction in ash is 43%.

When raw coal contains 20% ash, the reduction in ash is 53%.

When raw coal contains 2% sulphur, the reduction in sulphur is 13%.

When raw coal contains 3% sulphur, the reduction in sulphur is 17%.

When raw coal contains 4% sulphur, the reduction in sulphur is 22%.

When raw coal contains 5% sulphur, the reduction in sulphur is 28%.

4. The material rejected by the washing jig contains  $\frac{2}{3}$  coal and  $\frac{1}{3}$  noncombustible refuse.

5. One-fourth of the coal tested may be used for the manufacture of coke.

6. The evaporative efficiency of Illinois coal when burned in a hand-fired furnace under a water-tube boiler averages 62.7 per cent. This performance compares favorably with that of any other bituminous coal tested at the United States Geological laboratory.

7. The evaporative efficiency of Illinois coal is but slightly affected by the moisture contained in it.

8. The evaporative efficiency of Illinois coal decreases as the ash and sulphur increase. Each additional per cent of ash and sulphur results in 0.4 per cent decrease in efficiency.

9. The evaporative efficiency of Illinois coal, when burned in a hand-fired furnace, decreases as the per cent of fine coal contained in it increases.

10. Briquetting improves the evaporative efficiency of Illinois coal only when the raw coal is in the form of slack or screenings.

11. The performance of Illinois coal in a gas producer compares favorably with that of any other bituminous coal tested at the United States Geological Survey laboratory.

12. The value of Illinois coal as fuel for a gas-producer

---

\*Professor Parr's classification of coal, see page 11 of this circular.

decreases as the ash contained in it increases and as the calorific value decreases.

13. In small plants it requires at least two and one-half times as much coal to develop one horse-power when used in steam boiler service as when used in gas producer service.

14. Gas producers can be continuously operated with Illinois coal developing one electrical horse-power with 1.7 lb. of dry coal.

### III THE COALS TESTED

1. *The mining centers and districts of Illinois*, recognized by the trade and defined with reference to geographical position, have been described as follows.\*

(a) Williamson, Franklin, and Perry Counties. Williamson County led the production of the State in 1907 with more than 5,500,000 tons. No. 7, the Blue Band seam, which is from 5 to 10 feet thick, averaging 9 feet over a large area, is the greatest producer. It maintains an approximate uniformity in physical character and thickness but varies from place to place in fuel value. At Spillertown another seam, 4 feet thick, is mined 60 feet below No. 7. This seam is probably equivalent to No. 5 of Saline County and may have a wide distribution in the Williamson County district.

(b) Sangamon, Macoupin, Christian, Logan, and Macon Counties. The Springfield district, extending into several adjoining counties, has long been one of the most important. Sangamon produced more than 5,000,000 tons in 1907. The coal of the district is commonly known as No. 5, though recent work tends to confirm the suggestion that there are probably two distinct beds mined in this district,—No 5, in the area north of Chatham, and in No. 6 south of that town. The average thickness is a little less than 6 feet at Springfield, about 4.5 feet at Decatur and from 6 to 8 feet in Macoupin County.

(c) St. Clair, Madison, Clinton, and Randolph Counties. St. Clair County produced more than 4,500,000 tons in 1907. This district, known as the Bellville district, is not sharply set off from its neighbors since the same coal bed is mined under similar conditions in adjoining counties. It is the Blue Band seam and has a thickness of from 5 to 7 feet over much of the area. The seam is reached by shafts from 100 to 300 feet deep.

---

\*The Coal Resources of Illinois, by Frank W. DeWolf, Amer. Inst. of Mining Engineers, October, 1908,

(d) Vermilion County. During 1907 Vermilion County produced nearly 3,000,000 tons. It has long been an important area, shipping principally to the Chicago market. There are three persistent seams, two of which are worked. The top or Danville, No. 7, appears west of Vermilion river and is mined along the outcrop and by shafts from 75 to 200 feet deep. The other, known as the Grape Creek coal, No. 6, lies from 20 to 80 feet below the Danville and is the more important of the two.

(e) Saline County. Saline County is one of the newest and most rapidly growing producers. In 1907 its output was about 2,125,000 tons, a gain of 125 per cent over 1906. There are two seams, No. 7 and No. 5, underlying the northern two-thirds of this county and much of Gallatin on the east, each approximately 5 feet thick and lying 90 to 150 feet apart vertically.

(f) Fulton and Peoria Counties. Fulton County produced more than 2,000,000 tons in 1907 and Peoria about half as much. Here the principal seam, called No. 5, is from 4 to 4.5 feet thick. Shafts reach the coal at from 75 to 150 feet. In all, seven beds are present.

(g) La Salle, Bureau and Grundy Counties. The La Salle district includes three principal counties and produces more than 5,000,000 tons yearly. The largest production is by long-wall mining from seam No. 2, or the Third Vein. The coal averages 3 feet thick and is of good quality. About 140 feet above it, lies seam No. 5. It is about 4 feet thick. About 40 feet above No. 5 is seam No. 7. This is extensively mined by room-and-pillar methods.

2. *The samples tested* were procured from 5 of the 7 districts described in the preceding paragraph. They were furnished by the several coal mining companies of the state free of cost, and were shipped to the fuel testing laboratory under the supervision of an expert inspector whose chief care was to secure a sample for testing which fairly represented the normal product of the mine. The cars were numbered consecutively in the order of shipment, and this number has been retained as the laboratory designation of the sample. When two or more car lots consisting of different grades, such as lump, nut, etc., were shipped from the same mine, each lot was designated by a letter. For example, Illinois 11A is screened coal, 11B run-of-mine and 11C No. 5 washed coal, all from the same mine.

A complete list of the car-load samples of Illinois coal received and tested is given in Table 1. In this table the location

TABLE 1 SAMPLES OF ILLINOIS COAL TESTED


6

U. S. G. S. Number	Coal Bed or Seam	Location of Mine	County	Operator	Name or Number of Mine	Depth of Mine, feet
1	2	3	4	5	6	7
1	6	O'Fallon .....	St. Clair .....	Western Anthracite Coal and Coke Co. ....	Nigger Hollow No. 1. ....	.....
2	6	Marion .....	Williamson .....	Southern Illinois Coal Co. ....	No. 3. ....	.....
3	7	Troy .....	Madison .....	Donk Brothers Coal and Coke Co. ....	No. 3. ....	.....
4	7	Collinsville .....	Montgomery .....	Clover Leaf Coal Co. ....	No. 1. ....	.....
5	6	Coffeen .....	Montgomery .....	Clover Leaf Coal Co. ....	Clover Leaf Shaft No. 1. ....	.....
6A	5	Near Collinsville .....	Madison .....	Lamaghi Coal Co. ....	No. 2. ....	.....
6B	5	.....	.....	.....	No. 2. ....	.....
7A	6	.....	.....	.....	No. 2. ....	.....
7B	6	.....	.....	.....	No. 2. ....	.....
7C	6	.....	.....	.....	No. 2. ....	.....
7D	6	.....	.....	.....	No. 2. ....	.....
7E	6	.....	.....	.....	No. 2. ....	.....
8	6	Paisley .....	Montgomery .....	Dering Coal Co. ....	Paisley. ....	.....
9A	6	Near Staunton .....	Macoupin .....	Mt. Olive and Staunton Coal Co. ....	No. 2. ....	.....
9B	6	.....	.....	.....	No. 2. ....	.....
10	7	West Frankfort .....	Franklin .....	Dering Coal Co. ....	West Franklin. ....	.....
11A	7	Near Carterville .....	Williamson .....	St. Louis and Big Muddy Coal Co. ....	Daws Shaft. ....	.....
11B	7	.....	.....	.....	.....	.....
11C	7	.....	.....	.....	.....	.....
11D	7	.....	.....	.....	.....	.....
12A	7	Bush .....	.....	Western Coal and Mining Co. ....	Bush No. 1. ....	.....
12B	7	.....	.....	.....	.....	.....
13	7	Benton .....	Franklin .....	The Benton Coal Co. ....	Benton. ....	.....
14	5	East Side of Springfield .....	Sangamon .....	Capital Coal Co. ....	No. 2. ....	.....
15	6	Centralia .....	Marion .....	Peetinger and Davis. ....	South. ....	.....
16	7	Herrin .....	Williamson .....	Big Muddy Coal and Iron Co. ....	No. 7. ....	.....
18	8	La Salle .....	La Salle .....	La Salle County Carbon Coal Co. ....	La Salle Shaft. ....	.....
19A	7	Zeigler .....	Franklin .....	Zeigler Coal Co. ....	Zeigler. ....	.....
19B	7	.....	.....	.....	.....	.....
19C	7	.....	.....	.....	.....	.....
19D	7	.....	.....	.....	.....	.....
19E	7	.....	.....	.....	.....	.....
20	6	Staunton .....	Macoupin .....	.....	.....	.....
21	6	Troy .....	Madison .....	.....	.....	275

ILLINOIS ENGINEERING EXPERIMENT STATION

22A	6	Maryville.....	"			260
22B	6	"	"			260
23A	6	Donkville.....	"			145
23B	6	"	"			145
24A	6	New Baden.....	Clinton.....			320
24B	6	"	"			320
25A	6	Germantown.....	"			345
25B	6	"	"			345
26	5	Lincoln.....	Logan.....			276
27	6	Auburn.....	Sangamon.....			
28A	7	Herrin.....	Williamson.....			167
28B	7	"	"			167
28C	7	"	"			167
29A	5	Livingston.....	Madison.....			286
29B	5	"	"			286
30	7	Shiloh Station.....	St. Clair.....			126
31	6	Warder.....	"			300
33	7	Trenton.....	Clinton.....			320
34A	5	Harrisburg.....	Saline.....			165
34B	5	"	"			165





of the mine, the geological bed or seam and the name of the mine or its depth are given. Referring to the table it will be seen that fifty-three car samples from thirty-three different mines were tested, and that the mines are distributed throughout twelve of the principal coal mining counties of the State. The location of each mine is plotted on the map, Fig 1.

A comparison of the coal output of the several localities designated in paragraph 2, with the number of mines submitting samples, shows that the coal tested is fairly representative and while it is true that two comparatively important coal producing localities are not included, the results of tests should be accepted as characteristic of Illinois coal in general.

3. *The plan of the tests* as adopted by the United States Geological Survey included a complete chemical analysis of samples submitted, an investigation of the advantages of washing, an investigation of the coking qualities of the coal, and a series of boiler and gas producer trials. In carrying out this plan each sample was tested under conditions as nearly identical as possible, and every effort was made to secure results which would admit of direct comparison.

#### IV CHEMICAL PROPERTIES OF THE COALS TESTED

To determine the chemical properties of the coals tested, samples were taken both from the working face of the mine and from each car-load shipped.

4. *The mine samples* were obtained as follows: After a general inspection of the mine to determine the variations of coal in thickness and in quality, two representative points were selected in opposite parts of the mine. The face of the coal at these places was cleaned in order to remove any weathered coal or powder smoke, and a cut made across the face of the coal from roof to floor, including all the benches mined and such impurities as were not removed in ordinary work. The coal obtained, amounting to 25 or 30 pounds, was pulverized and quartered down according to generally accepted rules, and the sample placed in an air-tight iron can. This was mailed to the chemical laboratory where it was received and analyzed within two or three days.



5. *The car samples* were obtained during the process of unloading at the testing plant. A quantity never less than 200 pounds and often as great as 600 pounds was collected, a shovelful at a time from every part of the car. This was thoroughly crushed and quartered down until 25 or 30 pounds remained, placed in an airtight can and immediately shipped to the chemical laboratory. Here the sample was pulverized and again quartered until a convenient amount for analysis was obtained.

6. *The chemical work* included calorific determinations, and ultimate and proximate analyses. The calorific value was determined in duplicate for each car sample. A determination was also made for one of the two mine samples corresponding to each carload. An ultimate analysis was made in duplicate on each car sample. The approximate analysis and the determination of sulphur were made for practically every sample that came into the laboratory, and were made in duplicate for all car samples.

7. *The results of the chemical analyses* are given in Tables 2 and 3, (p. 12, et seq.) Column 1 gives the laboratory number, Column 2 the U. S. G. S. number, Column 3, the coal bed or seam and Column 4, the location from which the sample was taken. Column 5 gives the designation of the sample. The proximate analysis is given in Columns 6 to 14. These results are given both for air-dry coal (Columns 7 to 10) and for pure coal (Columns 12 to 14). The calorific value is given in terms of dry coal in Column 11 and in terms of pure coal in Column 15. Referring to the latter it will be seen that the maximum value is 14900 and the minimum 13900, a range of about 6.7 per cent. The average, however, is 14319 and but few of the recorded values vary from this by an amount greater than two per cent. The ultimate analysis is given in Columns 16 to 21. For convenience in comparing the results this is put in terms of dry coal. Columns 22, 23 and 24 have been calculated from the ultimate and proximate analyses. The combustible volatile is equal to the difference between the total volatile (Column 12) and the inert volatile (Column 23). The inert volatile is equal to 100 minus the total carbon, the ash, the water, the sulphur and the available hydrogen all divided by 100 minus the ash and water. The ratio of the volatile carbon to the total carbon (Column 24) is equal to total carbon as shown by the ultimate analysis minus the fixed carbon as shown by the proximate analysis divided by the total carbon.



The values included in Columns 22, 23 and 24 have been calculated in order to make possible a classification based on the ratio of volatile carbon to total carbon. This is the classification suggested by Professor S. W. Parr, and, in brief, is as follows.\*

COAL	Anthracite	Anthracite Proper.....Ratio $\frac{VC}{C}$ below 4%
		Semi-Anthracite.....Ratio $\frac{VC}{C}$ between 4% and 8%
		Semi-Bituminous.....Ratio $\frac{VC}{C}$ between 10% and 15%
	Bituminous Proper	A { Ratio $\frac{VC}{C}$ from 20% to 32% Inert Volatile from 5% to 10%
		B { Ratio $\frac{VC}{C}$ from 20% to 27% Inert Volatile from 10% to 16%
		C { Ratio $\frac{VC}{C}$ from 32% to 44% Inert Volatile from 5% to 10%
		D { Ratio $\frac{VC}{C}$ from 27% to 44% Inert Volatile from 10% to 16%
	Black Lignites	{ Ratio $\frac{VC}{C}$ from 27% up Inert Volatile from 16% to 20%
	Brown Lignites	{ Ratio $\frac{VC}{C}$ from 27% up Inert Volatile from 20% to 30%

It will be seen that in this system of classification all samples of Illinois coal tested fall in one of two divisions, bituminous B and bituminous D. In Table IV (p. 18) they have been arranged in the order of their volatile-carbon total-carbon ratio. Referring to Column 2 of this table the minimum value of the ratio  $\frac{VC}{C}$  is 20.9 and the maximum 33.4. The inert volatile calculated on the pure coal basis varies from 12.5 to 16.3.

The classification of the several coal beds or seams of the state as used in the state coal reports has often been questioned; nevertheless it is of interest to note that in so far as the present tests can be taken as an index, seam No. 7 falls in Class B, and seam No. 6 falls in Class D. Furthermore if, as has been pointed out, (paragraph 2, section b, Chapter II) certain of the Blue Band

\*Composition and Character of Illinois Coals, by S. W. Parr, Illinois State Geological Survey, Bulletin No. 8.

TABLE 2 CHEMICAL ANALYSES

Laboratory No.	U. S. G. S. No.	Coal Bed or Seam	County in Which Mine is Located	Designation of Sample	Loss in Moisture in Air-Drying, Per cent	Proximate Analysis of Air-Dry Coal, Per cent				B. t. u. per pound of Air-dry Coal	Proximate Analysis of Pure Coal (Ash and Moisture Free), Per cent			B. t. u. per pound of Pure Coal
						Moisture	Volatile Matter	Fixed Carbon	Ash		Volatile Matter	Fixed Carbon	Sulphur	
1	2	3	4	5	6	7	8	9	10	11	12	13	14	15
1	1	6	St. Clair	Mine Sample No. 1	4.40	7.08	41.12	41.00	10.80	11738	50.1	49.9	5.36	14294
2	1	6	"	Mine Sample No. 2	3.20	7.09	41.66	40.85	10.40	.....	50.4	49.6	5.05	14310
3	1	6	"	Car Sample	3.70	6.28	38.92	41.08	13.72	11448	48.6	51.4	3.32	13963
4	2	6	"	"	7.10	5.31	34.29	36.24	24.16	9848	48.6	51.4	6.10	14490
5	3	7	Williamson	Mine Sample No. 1	1.50	6.09	32.16	54.49	7.26	12556	37.2	62.8	1.15	14678
6	3	7	"	Mine Sample No. 2	1.80	5.63	34.92	51.78	7.67	.....	40.3	59.7	2.49	14678
7	3	7	"	Car Sample	2.70	5.96	30.20	52.16	11.59	12103	36.8	63.2	1.17	14678
8	4	7	Madison	Mine Sample No. 1	3.20	12.28	32.02	48.03	7.67	11520	40.0	60.0	.94	14390
9	4	7	"	Mine Sample No. 2	3.00	11.77	33.18	45.97	9.08	.....	41.8	58.2	1.99	.....
10	4	7	"	Car Sample	1.70	11.40	32.59	44.30	11.85	.....	42.4	57.6	1.74	14079
11	5	6	"	"	12.50	5.16	34.98	40.67	19.19	10651	46.1	53.9	4.66	14262
12	6	5	Montgomery	Mine Sample No. 1	5.60	9.84	36.86	44.96	8.34	11693	45.1	54.9	5.10	.....
13	6	5	"	Mine Sample No. 2	4.00	10.38	38.85	42.94	11.36	.....	45.1	54.9	5.55	.....
14	6A	5	"	Car Sample A	9.80	5.13	32.68	47.46	14.73	.....	40.8	59.2	5.55	14280
15	6	5	"	Mine Sample No. 3	6.60	12.90	33.77	42.25	11.08	10856	44.4	55.6	4.97	14280
16	6B	5	"	Car Sample B	8.10	11.93	29.99	43.90	14.18	10303	40.6	59.4	5.81	13943
17	7	6	Madison	Mine Sample No. 1	5.90	12.27	37.22	39.16	11.35	.....	48.7	51.3	6.11	14068
18	7	6	"	Mine Sample No. 2	5.90	11.87	36.57	39.98	11.58	10768	47.7	52.3	6.21	14068
19	7B	6	"	Car Sample B	5.00	11.46	34.98	36.25	17.31	10026	49.1	50.9	6.17	14075
20	7D	6	"	Car Sample D	3.50	10.83	36.24	39.75	13.18	10816	47.7	52.3	5.96	14233
21	8	6	Montgomery	Car Sample	4.40	13.20	34.33	33.94	12.53	10514	46.2	53.8	5.90	14156
22	9	6	Macoupin	Mine Sample No. 1	7.70	13.29	37.07	40.74	8.90	11162	47.6	52.4	5.30	14345
23	9	6	"	Mine Sample No. 2	7.70	15.27	36.19	39.34	9.20	.....	47.9	52.1	4.90	.....
24	9A	6	"	Car Sample A	9.00	13.54	35.56	40.03	10.74	10807	47.0	53.0	5.33	14297
25	9B	6	"	Car Sample B	10.10	13.72	36.24	39.72	10.32	10870	47.7	52.3	5.21	14310
26	9C	6	"	Car Sample C	13.30	15.25	28.57	40.83	15.35	9790	41.2	58.8	4.58	14107
27	10	7	Franklin	Car Sample	6.90	9.50	31.98	47.08	11.44	11506	40.4	59.6	1.83	14553
28	11	7	Williamson	Mine Sample	4.90	8.30	33.75	48.69	9.26	11999	41.0	59.0	3.42	14553

29	11A	7	Williamson	Car Sample A	4.80	7.76	31.44	50.19	10.61	11957	38.5	61.5	2.41	14618
30	11B	7	"	Car Sample B	5.80	8.86	31.25	48.23	11.06	11702	39.3	60.7	3.10	14723
31	11C	7	"	Car Sample C (washed coal)	6.40	8.61	32.40	51.33	7.66	12236	38.7	61.3	1.97	14613
32	12	7	"	Mine Sample No. 1	5.20	8.25	31.19	49.69	10.83	11837	38.5	61.5	3.47	14635
33	12	7	"	Mine Sample No. 2	5.60	8.41	34.27	45.44	11.88	.....	43.0	57.0	4.56	.....
34	12A	7	"	Car Sample A	3.60	8.20	32.26	46.59	12.95	11362	40.9	59.1	4.42	14410
35	12B	7	"	Car Sample B (washed coal)	13.30	15.87	28.19	46.42	9.52	10784	37.7	62.3	3.14	14454
36	12B	7	"	"	9.00	12.61	30.08	46.81	10.50	11065	39.1	60.9	3.08	14391
37	12B	7	"	"	12.40	15.31	28.93	45.29	10.47	10820	39.0	61.0	3.13	14578
38	13	7	Franklin	Mine Sample No. 1	5.30	10.28	32.04	49.74	7.94	.....	39.2	60.8	1.30	.....
39	13	7	"	Mine Sample No. 2	5.20	9.46	33.55	48.87	8.12	11990	40.7	59.3	1.98	14547
40	13	7	"	Car Sample	4.60	8.31	31.65	49.56	10.48	11727	39.0	61.0	1.91	14440
41	14	5	Sangamon	Mine Sample No. 1	10.80	13.89	33.96	40.89	11.26	10636	45.2	54.8	5.12	14201
42	14	5	"	Mine Sample No. 2	11.20	14.45	34.79	40.10	10.66	.....	46.4	53.6	4.62	.....
43	14	5	"	Car Sample	8.00	12.77	34.68	40.77	11.78	10757	45.9	54.1	5.51	14257
44	15	6	Marion	Mine Sample No. 1	7.20	10.25	37.43	39.79	12.53	11077	48.5	51.5	4.79	14315
45	15	6	"	Mine Sample No. 2	7.80	11.88	35.84	43.45	8.83	.....	45.2	54.8	4.10	.....
46	15	6	"	Car Sample	4.20	9.95	34.76	42.06	13.23	10960	45.2	54.8	5.04	14267
47	16	7	Williamson	Mine Sample No. 1	5.70	9.37	30.69	52.57	7.37	12058	36.8	63.2	1.40	14482
48	16	7	"	Mine Sample No. 2	4.80	8.59	31.07	53.37	6.97	.....	36.8	63.2	2.12	.....
49	16	7	"	Car Sample	4.00	8.43	30.08	51.89	9.60	11959	36.7	63.3	1.39	14589
50	18	2	La Salle	Mine Sample No. 1	11.00	13.87	37.26	38.56	10.31	10985	49.2	50.8	4.53	14488
51	18	2	"	Mine Sample No. 2	11.20	15.55	36.21	40.66	7.58	.....	47.1	52.9	3.91	.....
52	18	2	"	Car Sample	8.40	12.39	36.89	41.80	8.92	11399	46.9	53.1	4.98	14486
53	19	7	Franklin	Mine Sample No. 1	5.20	9.90	28.67	53.69	7.74	12001	34.81	65.2	.58	14571
54	19	7	"	Mine Sample No. 2	5.60	10.53	29.06	53.01	7.40	.....	35.4	64.6	.57	.....
55	19A	7	"	Car Sample A	9.10	14.91	26.66	49.50	8.93	10953	35.0	65.0	.68	14388
56	19B	7	"	Car Sample B	5.60	10.72	29.86	50.06	9.36	11686	37.4	62.6	1.14	14622
57	19C	7	"	Mine Sample No. 3	.....	9.65	30.87	53.22	6.25	.....	36.8	63.2	.57	.....
58	20	6	Macoupin	Mine Sample	12.40	16.68	31.32	40.32	13.68	10053	43.8	56.2	5.43	14033
59	21	6	Madison	Mine Sample No. 1	10.50	15.22	31.42	44.32	9.03	10901	41.5	58.5	2.10	14392
60	21	6	"	Mine Sample No. 2	13.30	17.79	28.78	42.34	11.09	.....	40.4	59.6	1.97	.....
61	21	6	"	Car Sample	10.40	15.54	31.28	42.27	10.93	10507	42.5	57.5	1.88	14289
62	21	6	"	Car Sample	8.20	15.30	30.59	43.40	10.71	.....	41.3	58.7	1.93	.....
63	22	6	"	Mine Sample No. 1	6.20	13.51	34.64	41.70	10.15	10881	45.4	54.6	5.25	14253
64	22	6	"	Mine Sample No. 2	9.90	13.83	34.16	42.24	9.77	.....	44.7	55.3	5.37	.....
65	22A	6	"	Car Sample A	5.90	11.91	35.65	39.43	13.01	10615	47.5	52.5	7.11	14138
66	22B	6	"	Car Sample B	11.20	13.03	32.65	39.79	14.53	10191	45.1	54.9	6.00	14008
67	23	6	"	Mine Sample No. 1	8.90	13.07	34.85	42.02	10.06	10949	45.3	54.7	4.67	14243
68	23	6	"	Mine Sample No. 2	9.70	12.79	35.67	40.25	11.29	.....	47.0	53.0	5.19	.....
69	23A	6	"	Car Sample A	11.50	13.47	34.35	40.65	11.53	10510	45.8	54.2	5.88	14013
70	23B	6	"	Car Sample B	13.20	15.68	31.28	37.45	15.59	9655	45.5	54.5	5.79	14048
71	24	6	Clinton	Mine Sample No. 1	10.10	13.43	33.02	44.37	9.18	10937	42.7	57.3	4.33	14132
72	24	6	"	Mine Sample No. 2	9.60	12.73	33.35	44.32	9.60	.....	42.9	57.1	4.64	.....
73	24B	6	"	Car Sample B	7.40	11.44	33.93	43.92	10.71	10958	43.6	56.4	6.35	14076
74	25	6	"	Mine Sample No. 1	6.70	11.64	35.41	44.29	8.66	11290	44.4	55.6	5.41	14166
75	25	6	"	Mine Sample No. 2	7.60	12.15	35.60	42.97	9.28	.....	45.3	54.7	5.10	.....
76	25B	6	"	Car Sample B	5.90	11.35	34.62	40.63	13.40	10733	46.0	54.0	6.33	14263
77	26	5	Logan	Mine Sample No. 1	11.30	14.77	32.90	39.75	12.58	.....	45.3	54.7	5.44	.....
78	26	5	"	Mine Sample No. 2	12.10	15.52	32.27	39.86	12.35	.....	44.7	55.3	5.06	.....
79	26	5	"	Car Sample	12.70	15.68	32.41	39.82	12.09	10215	44.8	55.2	4.86	14142
80	27	6	Sangamon	Mine Sample No. 1	10.20	14.29	37.17	40.36	8.18	11007	47.9	52.1	5.69	14197

TABLE 2 CHEMICAL ANALYSES (continued)

Laboratory No	U. S. G. S. No.	Coal Bed or Seam	County in which Mine is Located	Designation of Sample	Loss in Moisture in Air-Drying, Per cent	Proximate Analysis of Air-Dry Coal, Per cent				B. t. u. per pound of Air-dry Coal	Proximate Analysis of Pure Coal (Ash and Moisture Free), Per cent			B. t. u. per pound of Pure Coal
						Moisture	Volatile Matter	Fixed Carbon	Ash		Volatile Matter	Fixed Carbon	Sulphur	
1	2	3	4	5	6	7	8	9	10	11	12	13	14	15
81	27	6	Sangamon.....	Mine Sample No. 2.....	10.50	14.18	34.85	41.11	9.86	.....	45.9	54.1	5.74	.....
82	27	6	.....	Car Sample.....	10.00	16.00	32.41	37.82	13.77	9940	46.2	53.8	5.77	14153
83	28	7	Williamson.....	Mine Sample No. 1.....	.....	8.72	30.38	53.28	7.62	12200	38.3	63.7	1.20	14583
84	28	7	.....	Mine Sample No. 2.....	.....	8.88	29.49	53.60	8.03	.....	35.5	64.5	1.19	.....
85	28C	7	.....	Car Sample C.....	3.00	7.78	29.84	52.39	9.98	11959	36.3	63.7	1.49	14542
86	29	5	Madison.....	Mine Sample No. 1.....	.....	14.25	35.52	40.79	9.44	10892	46.6	53.4	4.88	14273
87	29	5	.....	Mine Sample No. 2.....	.....	12.69	37.40	41.15	8.76	11236	47.6	52.4	4.61	14304
88	29A	5	.....	Car Sample A.....	8.60	13.15	30.73	40.12	16.00	9983	43.4	56.6	5.88	14090
89	29B	5	.....	Car Sample B.....	7.30	12.47	33.12	41.85	12.56	10667	44.2	55.8	5.83	14228
90	29B	5	.....	Car Sample B.....	5.50	12.25	33.76	41.66	12.33	10719	44.7	63.3	5.86	14212
91	30	7	St. Clair.....	Mine Sample No. 1.....	2.30	10.73	39.60	40.41	9.26	.....	49.5	50.5	5.15	.....
92	30	7	.....	Mine Sample No. 2.....	.....	9.88	42.26	37.05	10.81	11439	53.3	46.7	4.83	14423
93	30	7	.....	Car Sample.....	8.70	11.69	35.70	39.42	13.19	10699	47.5	52.5	5.83	14243
94	31	6	.....	Mine Sample No. 1.....	8.00	13.17	34.79	41.75	10.29	.....	45.4	54.6	4.21	.....
95	31	6	.....	Mine Sample No. 2.....	9.40	14.38	33.92	42.95	8.75	10858	44.1	55.9	4.07	14125
96	31	6	.....	Car Sample.....	9.70	13.10	32.16	41.49	13.25	10363	43.7	56.3	4.97	14070
97	33	7	Clinton.....	Mine Sample No. 1.....	4.70	14.45	29.76	46.16	9.63	.....	39.2	60.8	2.75	.....
98	33	7	.....	Mine Sample No. 2.....	4.80	15.06	29.48	45.81	9.65	10726	39.1	60.9	1.39	14438
99	33	7	.....	Car Sample.....	.....	11.50	25.44	42.37	20.69	.....	37.5	62.5	2.24	.....
100	34	5	Saline.....	Mine Sample No. 1.....	4.20	7.55	33.85	51.45	7.15	.....	39.7	60.3	1.83	.....
101	34	5	.....	Mine Sample No. 2.....	.....	7.51	32.81	52.20	7.48	12686	38.6	61.4	1.86	14923
102	34A	5	.....	Car Sample A.....	6.60	9.33	30.92	47.86	11.89	11572	39.2	60.8	3.50	14189
103	34B	5	.....	Car Sample B.....	5.80	7.81	33.54	50.27	8.38	12418	40.0	60.0	2.82	14817

TABLE 3 CHEMICAL ANALYSES

[illegible]

TABLE 3 CHEMICAL ANALYSES (Continued)

Laboratory No.	U. S. G. S. No.	Coal Bed or Seam	Designation of Sample	Ultimate Analysis of Dry Coal (Per cent)						Combustible Volatile, (Pure Coal Basis)	Inert Volatile, (Pure Coal Basis)	Ratio of Volatile Carbon to Total Carbon
				Hydrogen	Carbon	Nitrogen	Oxygen	Sulphur	Ash			
1	2	3	5	16	17	18	19	20	21	22	23	24
29	11A	7	Car Sample A.....	4.93	72.15	1.43	7.85	2.14	11.50	26.9	11.6	24.6
30	11B	7	Car Sample B.....	4.67	70.54	1.41	7.88	2.70	12.80	27.5	11.8	25.0
31	11C	7	Car Sample C.....	4.84	70.56	1.46	8.95	1.81	8.38	26.1	12.6	24.7
32	12	7	.....	.....	.....	.....	.....	.....	.....	.....	.....	.....
33	12	7	.....	.....	.....	.....	.....	.....	.....	.....	.....	.....
34	12A	7	Car Sample A.....	4.55	68.11	1.20	8.25	3.79	14.10	27.7	12.7	25.5
35	12B	7	Car Sample B.....	4.71	70.91	1.26	9.16	2.78	11.18	24.7	13.0	22.2
36	12B	7	Car Sample B.....	4.54	71.13	1.06	8.55	2.71	12.01	27.0	12.1	24.7
37	12B	7	Car Sample B.....	4.61	70.73	1.23	8.35	2.73	12.35	26.9	12.1	22.7
38	13	7	.....	.....	.....	.....	.....	.....	.....	.....	.....	.....
39	13	7	.....	.....	.....	.....	.....	.....	.....	.....	.....	.....
40	13	7	Car Sample.....	4.65	71.97	1.61	8.83	1.69	11.43	26.0	13.0	24.7
41	14	7	.....	.....	.....	.....	.....	.....	.....	.....	.....	.....
42	14	7	.....	.....	.....	.....	.....	.....	.....	.....	.....	.....
43	14	7	Car Sample.....	4.67	67.33	1.25	8.48	4.77	13.15	33.5	12.4	30.6
44	15	7	.....	.....	.....	.....	.....	.....	.....	.....	.....	.....
45	15	7	.....	.....	.....	.....	.....	.....	.....	.....	.....	.....
46	15	7	Car Sample.....	4.61	66.22	1.15	9.02	4.30	14.70	32.0	13.2	29.5
47	16	7	.....	.....	.....	.....	.....	.....	.....	.....	.....	.....
48	16	7	.....	.....	.....	.....	.....	.....	.....	.....	.....	.....
49	16	7	Car Sample.....	4.63	73.51	1.64	8.47	1.25	10.49	24.2	12.5	22.9
50	18	7	.....	.....	.....	.....	.....	.....	.....	.....	.....	.....
51	18	7	.....	.....	.....	.....	.....	.....	.....	.....	.....	.....
52	18	7	Car Sample.....	5.10	69.95	1.14	9.15	4.47	10.18	34.2	12.7	31.8
53	19	7	Mine Sample No. 1.....	.....	.....	.....	.....	.....	.....	.....	.....	.....
54	19	7	Mine Sample No. 2.....	.....	.....	.....	.....	.....	.....	.....	.....	.....
55	19A	7	Car Sample A.....	4.42	73.75	1.59	9.13	.61	10.50	21.7	13.3	21.0
56	19B	7	Car Sample B.....	4.60	74.76	1.57	7.57	1.02	10.48	26.1	11.3	25.0

57	19C	7	Mine Sample No. 3.....	.....	.....	.....	.....	.....	.....	.....	.....	.....
58	20	6	Mine Sample.....	4.43	64.71	1.17	9.11	4.55	16.03	30.2	13.6	26.9
59	21	6	Mine Sample No. 1.....	.....	.....	.....	.....	.....	.....	.....	.....	.....
60	21	6	Mine Sample No. 2.....	.....	.....	.....	.....	.....	.....	.....	.....	.....
61	21	6	Car Sample A.....	4.57	68.70	1.29	10.86	1.63	12.95	26.2	16.3	23.7
62	21	6	Car Sample B.....	.....	.....	.....	.....	.....	.....	.....	.....	.....
63	22	6	Mine Sample No. 1.....	.....	.....	.....	.....	.....	.....	.....	.....	.....
64	22	6	Mine Sample No. 2.....	.....	.....	.....	.....	.....	.....	.....	.....	.....
65	23A	6	Car Sample A.....	4.42	65.10	1.14	8.51	6.06	14.77	34.9	12.6	31.3
66	23B	6	Car Sample B.....	4.37	64.33	1.02	8.58	5.00	16.70	32.3	12.8	27.1
67	23	6	Mine Sample No. 1.....	.....	.....	.....	.....	.....	.....	.....	.....	.....
68	23	6	Mine Sample No. 2.....	.....	.....	.....	.....	.....	.....	.....	.....	.....
69	23A	6	Car Sample A.....	4.77	66.58	1.05	9.18	5.19	13.32	32.3	13.5	29.4
70	23B	6	Car Sample B.....	4.37	62.72	1.06	8.64	4.72	18.49	33.3	13.20	29.2
71	24	6	Mine Sample No. 1.....	.....	.....	.....	.....	.....	.....	.....	.....	.....
72	24	6	Mine Sample No. 2.....	.....	.....	.....	.....	.....	.....	.....	.....	.....
73	24B	6	Car Sample B.....	4.65	67.81	1.15	8.71	5.52	12.10	31.1	12.5	26.9
74	25	6	Mine Sample No. 1.....	.....	.....	.....	.....	.....	.....	.....	.....	.....
75	25	6	Mine Sample No. 2.....	.....	.....	.....	.....	.....	.....	.....	.....	.....
76	25B	6	Car Sample B.....	4.68	64.70	1.19	8.95	5.37	15.11	32.6	13.4	29.2
77	26	5	Mine Sample No. 1.....	.....	.....	.....	.....	.....	.....	.....	.....	.....
78	26	5	Mine Sample No. 2.....	.....	.....	.....	.....	.....	.....	.....	.....	.....
79	26	5	Car Sample.....	4.53	67.31	1.26	8.40	4.16	14.34	32.3	12.5	29.8
80	27	6	Mine Sample No. 1.....	.....	.....	.....	.....	.....	.....	.....	.....	.....
81	27	6	Mine Sample No. 2.....	.....	.....	.....	.....	.....	.....	.....	.....	.....
82	27	6	Car Sample.....	4.49	64.15	1.08	9.06	4.83	16.39	32.7	13.5	29.8
83	28	7	Mine Sample No. 1.....	.....	.....	.....	.....	.....	.....	.....	.....	.....
84	28	7	Mine Sample No. 2.....	.....	.....	.....	.....	.....	.....	.....	.....	.....
85	28C	7	Car Sample C.....	4.55	73.15	1.31	8.74	1.43	10.82	23.8	12.5	20.9
86	29	5	Mine Sample No. 1.....	.....	.....	.....	.....	.....	.....	.....	.....	.....
87	29	5	Mine Sample No. 2.....	.....	.....	.....	.....	.....	.....	.....	.....	.....
88	29A	5	Car Sample A.....	4.37	62.43	1.02	8.96	4.80	18.42	29.6	13.8	26.1
89	29B	5	Car Sample B.....	4.56	65.31	1.14	9.65	4.99	14.35	30.2	14.0	26.8
90	29B	5	Car Sample B.....	4.65	66.43	.91	8.92	5.04	14.05	32.0	12.7	28.5
91	30	7	Mine Sample No. 1.....	.....	.....	.....	.....	.....	.....	.....	.....	.....
92	30	7	Mine Sample No. 2.....	.....	.....	.....	.....	.....	.....	.....	.....	.....
93	30	7	Car Sample.....	4.71	64.71	1.06	9.62	4.96	14.94	33.5	14.0	31.0
94	31	6	Mine Sample No. 1.....	.....	.....	.....	.....	.....	.....	.....	.....	.....
95	31	6	Mine Sample No. 2.....	.....	.....	.....	.....	.....	.....	.....	.....	.....
96	31	6	Car Sample.....	4.59	65.95	1.18	8.82	4.21	15.25	30.6	13.1	27.6
97	33	7	Mine Sample No. 1.....	.....	.....	.....	.....	.....	.....	.....	.....	.....
98	33	7	Mine Sample No. 2.....	.....	.....	.....	.....	.....	.....	.....	.....	.....
99	33	7	Car Sample.....	3.72	61.46	1.02	8.70	1.72	23.38	24.7	12.8	31.0
100	34	5	Mine Sample No. 1.....	.....	.....	.....	.....	.....	.....	.....	.....	.....
101	34	5	Mine Sample No. 2.....	.....	.....	.....	.....	.....	.....	.....	.....	.....
102	34A	5	Car Sample A.....	4.50	69.32	1.42	8.60	3.05	13.11	28.1	13.1	25.4
103	34B	5	Car Sample B.....	4.82	73.11	1.56	8.86	2.56	9.09	27.3	12.7	25.4

FUEL TESTS WITH ILLINOIS COAL

coals of Sangamon County in reality belong to Seam 6 instead of 5, Class B would also include all coals tested from seam No. 5. The single sample from Seam No. 2, (U. S. G. S. 18) falls in Class D, well up towards the lignites.

TABLE IV

CLASSIFICATION OF ILLINOIS COAL ON THE BASIS OF THE  
VOLATILE-CARBON AND TOTAL-CARBON RATIO

U. S. G. S. Number	Ratio of Volatile Carbon to Total Carbon	Inert Volatile (Pure Coal Basis)	Class	Coal Bed or Seam
1	2	3	4	5
28	20.90	12.50	B	7
6	22.20	13.35	B	5
3	22.50	12.20	B	7
16	22.90	12.50	B	7
19	23.00	12.30	B	7
12	23.63	12.20	B	7
21	23.70	16.30	B	6
13	24.70	13.00	B	7
11	24.77	12.00	B	7
34	25.40	12.90	B	5
10	26.20	13.30	B	7
24	26.90	12.50	D	6
20	26.90	13.60	D	6
29	27.13	13.50	D	5
31	27.60	13.10	D	6
4	28.30	12.30	D	6
9	29.00	13.00	D	6
22	29.20	12.70	D	6
23	29.30	13.30	D	6
25	29.20	13.40	D	6
15	29.50	13.20	D	6
26	29.80	12.50	D	5
27	29.80	13.50	D	6
8	30.30	12.70	D	6
14	30.60	12.40	D	5
30	31.00	14.00	D	6
33	31.00	12.80	D	7
18	31.80	12.70	D	2
7	32.80	12.95	D	6
1 & 2	33.40	12.95	D	6

## V WASHING TESTS

8. *The equipment for the washing tests* of Illinois coal consists of one modified Stewart jig and one jig especially designed for the laboratory, a Cornish tooth-roll crusher, an adjustable-mesh bumping screen, and bins of suitable capacity for storing the coal. The Stewart jig, shown in Fig. 2, provides for the washing of coal not exceeding  $1\frac{1}{2}$  inches in diameter. The special jig may be used for larger sizes. It is of the center-plunger type, that is, the plunger is directly beneath the screen. Its upward stroke causes the pulsation, and its downward stroke, by an arrangement of valves at the side of the jig body, admits the water sup-



ply. The screen is 4 feet wide by 5 feet long and is constructed of No. 10 wire set 1-16 inch apart. The length of stroke and the depth of the coal bed are adjustable.




FIG. 2 STEWART JIG (PROF. PAPER 48, p. 1460)

9. *The tests* involved the weighing of the raw and washed coal, and the refuse. Samples of the coal were collected before and after it was fed to the jig. These were sent to the chemical laboratory for analysis. Altogether 31 tests were made on 24 kinds of coal.

10. *The results of the tests* are given in Table 5. Column 1 of this table is the U. S. G. S. coal number, Column 2 the jig used

TABLE 5 WASHING TESTS

U. S. G. S. No.	Jig Used	Size of Coal	Proximate Analysis of Raw Coal, Percent					Proximate Analysis of Washed Coal, Percent			Raw Coal pounds	Washed Coal pounds	Refuse, Per cent of Raw Coal
			Moisture	Volatile Matter	Fixed Carbon	Ash	Sulphur (Separately Determined)	Moisture	Ash	Sulphur (Separately Determined)			
1	2	3	4	5	6	7	8	9	10	11	12	13	14
2	Stewart	Slack	12.03	.....	.....	22.44	4.00	19.07	9.42	3.35	27280	.....	.....
2	"	Run of Mine	.....	.....	.....	10.59	1.45	.....	5.86	1.41	.....	.....	.....
5	"	No. 5 Nut	.....	.....	.....	17.56	3.25	.....	9.18	2.71	.....	.....	.....
6	Stewart, modified	Run of Mine crushed to 2 in.	14.43	29.48	42.81	13.28	4.01	15.23	8.64	3.30	14710	13586	7.6
7C	"	Slack	10.69	23.08	36.14	20.09	4.06	15.64	8.59	3.25	15809	11238	28.9
7D	"	Run of Mine crushed to 2 in.	10.83	26.24	39.75	13.18	4.53	12.45	9.30	3.38	14000	11790	15.8
9A	"	"	13.54	35.69	40.03	10.74	4.03	15.65	7.57	3.38	18000	13920	22.7
10	"	Slack	9.50	31.98	47.08	11.44	1.45	11.86	6.67	1.38	14710	12785	13.0
12	"	Run of Mine crushed to 2 in.	8.20	32.26	46.59	12.95	3.48	13.30	8.91	2.48	18000	15900	11.7
13	"	Egg crushed to 2 in.	8.31	31.65	49.56	10.48	1.55	11.15	7.49	1.27	29950	27550	8.0
14	"	Lump crushed to 2 in.	12.77	34.68	40.77	11.78	4.16	16.32	9.37	3.20	18000	15955	11.4
15	"	Lump & Egg crushed to 2 in.	8.43	34.76	42.06	13.23	3.87	11.81	8.41	3.00	18000	13055	27.6
16	"	"	8.43	31.65	49.56	10.48	1.55	11.15	7.49	1.27	29950	27550	10.7
18	"	Lump crushed to 2 in.	12.39	36.89	41.80	8.92	3.32	14.99	5.77	2.98	18000	14400	20.0
20	"	Screenings crushed to 2 in.	14.68	31.32	40.32	13.68	3.88	16.80	10.26	3.21	63280	57000	10.0
21	"	Lump crushed to 2 in.	15.30	30.59	43.40	10.71	1.43	8.25	8.09	1.25	17000	14000	13.9
22A	"	"	11.91	35.65	39.43	13.01	5.34	14.02	8.58	3.03	19100	17000	12.4
22B	"	Nut & Slack crushed to 2 in.	13.03	32.65	39.79	14.53	4.35	16.78	9.99	3.73	40000	32000	20.0
23A	"	Lump crushed to 2 in.	13.47	34.35	40.65	11.53	4.41	13.81	8.78	3.54	28000	24000	14.3
23B	"	Screenings crushed to 2 in.	15.68	31.28	37.45	15.59	3.98	16.83	8.75	3.32	80000	63000	21.2
24A	"	"	11.44	33.93	43.92	10.91	4.94	15.10	9.75	3.18	20000	15000	25.0
24B	"	Nut crushed to 2 in.	11.44	33.93	43.92	10.91	4.94	14.36	8.38	3.31	18745	18660	11.1
25A	"	Run of Mine crushed to 2 in.	12.96	33.01	39.60	14.43	4.09	14.14	8.98	3.05	14558	12900	17.5
26	"	"	15.68	32.41	39.82	12.00	3.51	15.96	9.40	3.76	18000	16000	11.1
27	"	"	16.00	32.41	37.82	13.77	4.05	16.11	7.76	3.29	18000	15545	13.6
28C	"	Lump crushed to 2 in.	7.78	29.85	52.39	9.98	1.32	9.75	7.12	1.05	24000	19255	17.0
29A	"	Screenings crushed to 2 in.	13.10	30.73	40.12	16.00	4.17	15.88	7.70	3.06	18000	13750	23.6
29A	"	"	13.10	30.73	40.12	16.00	4.17	15.88	7.70	3.06	59500	41500	30.4
30	"	Nut crushed to 2½ in.	11.69	35.70	32.42	13.19	4.38	12.36	9.44	3.26	30000	23200	29.6
30	Special	Nut crushed to 1 in.	11.69	35.70	32.42	13.19	4.38	13.67	7.89	3.15	24900	20200	18.8
34A	"	Screenings crushed to 1 in.	9.33	30.92	47.86	11.89	2.76	8.68	7.44	2.19	43300	39100	20.7

and Column 3 the size of the coal. The proximate analysis of the raw and washed coal is given in Columns 4 to 11. The weight of raw coal tested is given in Column 12 and the washed coal produced in Column 13. Column 14 gives the refuse expressed in per cent of raw coal fed to the jig.

11. *The improvement in quality of the coal effected by washing is well shown in Columns 4 to 11. For example the per cent of ash content is, in every case, decreased by washing. This is shown graphically in Fig. 3. In this figure the per cent of ash in the washed coal is plotted against per cent of ash in the raw coal. The average line shows that by resorting to the process of washing, it is possible to reduce the ash content from 22 per cent to 8.7 per cent and from 10 per cent to 6.9 per cent. Expressed in per cent the amount of reduction is as follows:*

When raw coal contains 8% ash, the reduction is 20%.  
When raw coal contains 12% ash, the reduction is 30%.  
When raw coal contains 16% ash, the reduction is 43%.  
When raw coal contains 20% ash, the reduction is 53%.




FIG. 3 REDUCTION OF ASH DUE TO WASHING

In a similar way the reduction in sulphur due to washing is shown in Fig. 4. Referring to this figure it will be seen that:

When raw coal contains 2% sulphur, the reduction is 13%.

When raw coal contains 3% sulphur, the reduction is 17%.

When raw coal contains 4% sulphur, the reduction is 22%.

When raw coal contains 5% sulphur, the reduction is 28%.




FIG. 4 REDUCTION OF SULPHUR DUE TO WASHING

In bringing about this improvement in the quality of coal by washing, much good coal which can not be recovered is carried off with the refuse from the jig. For example, the tests show that, based on the average of all tests, the refuse amounts to 16.8 per cent of the raw coal. The ash in the raw coal is 12.6 per cent, but in the washed coal this is reduced to 8.34 per cent, therefore  $12.6 - 83.2 \times 8.34$  or 5.7 per cent is the ash content in the refuse. It appears, then, that the material thus discharged is made up of about  $\frac{2}{3}$  pure coal and  $\frac{1}{3}$  ash.

## VI COKING TESTS

12. *The ovens* in which tests of the coking qualities of the coal were made are of the regular beehive pattern. Originally they were arranged in a battery of three, two of standard size, 12 feet in diameter, by 7 feet high, and the third 12 feet in diameter by 6 feet 4 inches high; later, however, one of the standard ovens was removed. Since the two remaining ovens may be considered as end ovens, that is, those placed at the ends of the battery, the results obtained are directly comparable.

13. *The tests.*—To prepare the coal for test it was finely crushed in a Williams mill. It was then placed on the larry and delivered to the oven. The larry used when the work was begun had a capacity less than one ton. This necessitated the filling and emptying of the larry six or eight times before the charge was complete. Each portion thus had time to emit a large amount of gas and often to burst into flames before the next portion of the charge was added. This resulted in much injurious cross lamination of the coke in many of the earlier tests. Afterwards when a larger larry was installed and the time of charging reduced from one hour to less than seven minutes the laminations and cross-breakage disappeared.

Directly after drawing the charge the ovens were closed for a period of one or two hours during which time they were allowed to gather heat for the next charge.

A sample of coal was taken at regular intervals as the charge was emptied into the larry. The total weight collected was 40 or 50 pounds. A sample of coke was taken from 5 different parts of the oven, one piece 2 feet from the oven floor, one 2 feet from each side on a line drawn from the center of the oven, one from the center of the oven, and one 2 feet from the back wall. The separate pieces of coke extended the whole height of the charge and were as nearly uniform in size as possible.

14. *The results of the tests* are given in Table 6. Column 1 of this table is the test number, Column 2 the U. S. G. S. number, and Column 3 the size as shipped to the laboratory. The proximate analysis of the coal and coke produced from it is given in Columns 4 to 13. Column 14 gives the weight of coal in the charge. The coke produced in per cent of the weight of the coal charged is given in Column 15, and the per cent of breeze in Column 16. The total yield as given in Column 17 is the sum of the coke and breeze produced. A brief description of the physical

TABLE 6 COKING TESTS

Test No.	U. S. G. S. No.	Size of Coal	Proximate Analysis of Coal					Proximate Analysis of Coke				
			Moisture	Volatile Matter	Fixed Carbon	Ash	Sulphur Separately Determined	Moisture	Volatile Matter	Fixed Carbon	Ash	Sulphur Separately Determined
1	2	3	4	5	6	7	8	9	10	11	12	13
10	1	Lump and nut.....	10.46	36.11	37.48	15.95	4.14	....	....	....	....	....
9	2	Washed slack.....	17.20	35.77	37.84	9.19	3.03	1.57	2.83	75.42	20.18	2.75
29	3	Run of mine.....	8.25	30.32	50.95	10.59	1.45	....	....	....	....	....
28	3	Washed run of mine.....	9.52	32.05	52.57	5.86	1.41	6.11	.42	82.55	10.92	1.13
45	5	Washed slack.....	17.86	31.65	32.93	17.56	3.25	....	....	....	....	....
50	5	".....	25.15	28.68	36.99	9.18	2.71	....	....	....	....	....
60	5	".....	14.60	30.76	36.48	18.16	3.44	....	....	....	....	....
1	7D	Run-of-mine crushed.....	10.98	35.27	38.44	15.41	4.53	2.26	1.84	72.68	23.20	3.95
4	7D	Run-of-mine crushed and washed.....	12.45	36.17	42.08	9.30	3.64	1.04	.61	82.10	16.25	3.24
5	11D	No 3 crushed and washed.....	8.24	31.64	52.81	7.31	1.55	1.19	.93	85.97	11.91	1.44
3	13	Egg, crushed.....	10.56	30.08	49.08	10.28	1.71	2.73	1.36	79.30	16.61	1.77
2	13	Egg, crushed and washed.....	11.44	30.95	50.16	7.45	1.25	4.60	1.68	82.08	11.64	1.27
7	16	Lump and Egg crushed.....	....	....	....	....	....	....	....	....	....	....
10	16	Lump and Egg crushed and washed.....	9.79	30.35	51.79	8.07	1.09	2.14	1.46	83.96	12.44	1.02
11	19A	1/4 in. crushed.....	14.91	26.66	49.50	8.93	.52	....	....	....	....	....
15	19A	".....	14.91	26.66	49.50	8.93	.52	....	....	....	....	....
19	19B	3 in. Lump crushed.....	10.72	29.86	50.06	9.36	.91	....	....	....	....	....
106	20	Screenings crushed.....	17.04	32.59	40.77	9.60	3.23	0.57	.66	82.49	16.28	3.01
107	20	Screenings crushed and washed.....	14.36	34.61	42.63	8.40	3.23	0.53	.29	84.87	14.31	2.73
126	21	Lump crushed.....	13.37	31.17	43.15	12.31	1.46	....	....	....	....	....
127	21	Lump crushed and washed.....	17.45	30.01	44.24	7.80	1.10	....	....	....	....	....
117	22B	Screened Lump and Nut, crushed.....	11.98	33.87	37.72	16.43	4.74	.98	.72	72.18	26.12	4.61
118	22B	Screened Lump and Nut, crushed and washed.....	16.19	34.14	39.53	10.14	3.79	.65	1.60	80.76	16.99	3.65
111	23A	Lump crushed.....	13.74	36.47	41.01	8.78	3.57	.66	.74	83.45	15.15	3.09
112	23B	Slack.....	15.85	35.02	40.57	8.56	3.27	.96	1.14	82.66	15.24	2.87
114	23B	Slack.....	15.93	35.88	40.16	8.03	3.25	1.36	1.19	82.83	14.62	2.84
119	24A	Screenings.....	13.28	29.03	39.03	17.76	4.05	....	....	....	....	....
155	24A	Screenings crushed, washed.....	15.18	32.13	43.46	9.23	3.07	....	....	....	....	....
145	24B	Lump, crushed and washed.....	8.93	35.22	46.29	9.56	3.41	5.62	1.46	79.01	13.73	2.97
120	25A	Run of mine.....	12.96	33.01	39.60	14.43	4.09	....	....	....	....	....
140	25A	Run-of-mine crushed and washed.....	13.40	33.83	43.66	9.11	2.99	2.71	4.67	77.69	14.93	2.32
143	26	Run-of-mine washed and crushed.....	15.18	33.46	41.53	9.83	2.73	5.27	3.36	75.98	15.40	2.80
144	27	Run-of-mine crushed and washed.....	16.39	34.26	41.57	7.78	3.22	3.51	1.55	81.14	13.80	3.40
166	28C	Lump crushed and washed.....	9.37	30.38	53.36	6.89	1.09	2.82	.60	86.12	10.46	.98
169	29A	Screenings crushed and washed.....	15.63	33.88	42.81	7.68	3.13	.72	.90	84.62	13.76	2.57
170	29A	".....	18.39	32.87	41.53	7.21	3.06	2.78	.74	83.35	13.13	2.49
190	34B	Run-of-mine crushed and washed.....	9.91	33.33	50.65	6.11	1.75	.19	.35	87.91	11.55	1.48

TABLE 6 COKING TESTS (Continued)

Test No.	U. S. G. S. No.	Coal Charged pounds	Coke Produced per cent	Breeze Produced per cent	Total Yield per cent	REMARKS
1	2	14	15	16	17	18
10	1	9000	0	0	0	No valuable coke produced.....
9	2	9000	37.6	3.9	41.5	Poor dark colored coke.....
29	3	9000	0	0	0	No coke produced.....
28	3	13000	49.0	6.4	55.4	Comparatively good, light colored coke; brittle and friable.....
45	5	8000	0	0	0	No coke produced.....
59	5	5000	0	0	0	..
60	5	9000	0	0	0	..
1	7D	8000	48.84	5.65	54.49	Good hard coke; sulphur and ash too high.....
4	7D	8000	52.00	2.60	54.60	Good strong, light colored coke; sulphur too high.....
5	11D	10000	54.00	3.00	57.00	Good strong, light colored coke.....
3	13	12000	44.65	11.06	55.71	Dull colored, comparatively soft coke.....
2	13	10000	46.00	7.18	53.18	Good hard coke.....
7	16	.....	.....	.....	.....	Test discontinued on account of accident.....
10	16	10000	55.79	9.10	64.89	Dull gray colored; poor coke physically.....
11	19A	10000	0	0	0	No coke produced.....
15	19A	6000	0	0	0	..
19	19B	6000	0	0	0	..
106	20	10000	42.55	6.28	48.83	Poor, dull gray coke.....
107	20	10000	46.59	3.98	50.57	Dull gray coke. Slightly better physically than coke from unwashed coal.....
126	21	12000	0	0	0	No coke produced.....
127	21	11690	0	0	0	..
117	22B	10000	50.46	5.34	55.80	Poor, dull gray coke.....
118	22B	12000	46.80	4.78	51.58	Light colored, comparatively good coke.....
111	23A	10000	42.11	3.47	45.58	Good, light colored, heavy coke.....
112	23B	10000	44.07	3.89	47.96	..
114	23B	14000	46.02	4.29	50.31	Fairly good, light colored coke.....
119	24A	10000	0	0	0	No coke produced.....
155	24A	11410	0	0	0	..
145	24B	11830	39.81	11.41	51.22	Poor, soft, dense, coke.....
120	25A	10000	0	0	0	No coke produced.....
140	25A	11830	45.27	6.00	51.27	Poor, soft, dense, dull colored coke.....
143	26	11750	49.79	10.64	60.43	Dense, soft, coke.....
144	27	11550	43.87	3.51	47.38	..
166	28C	12600	50.40	5.25	55.65	Poor dense, dark colored, soft coke.....
169	29A	12310	41.22	5.70	46.92	Poor dense, coke.....
170	29A	11680	42.38	2.89	45.27	..
190	34A	12980	50.25	2.43	52.68	Good light colored coke.....

properties of the coke produced is given in Column 18.

In reviewing the results of the tests as set forth in Table 6, it should be remembered that the necessary routine work involved in the testing of so many coals made it possible to make but few tests on each coal. The data presented, therefore, show the results obtained under conditions which of necessity had to be controlled by observations made from time to time as the coking proceeded, a procedure which tended to make the conditions of operations by no means ideal.

Of the 37 tests made with Illinois coal 9 resulted in the production of comparatively good coke and 14 in the production of a poor grade of coke. The remaining 14 samples apparently proved to be non-coking coals. Referring to the approximate analyses of the coke produced it will be seen that in a number of cases the quality of the coke is by no means inferior, though in all cases the ash and sulphur content is slightly greater than is desirable. Seven samples (11D washed, 13, 13 washed, 16, 22B washed, and 29 washed) were successfully used in a foundry cupola.

## VII STEAMING TESTS

15. *The apparatus comprising the plant for steaming tests consisted of two standard Heine water-tube boilers equipped with hand-fired furnaces and an Allis-Chalmers Corliss engine operating a 200 kilowatt Bullock generator. A plan and elevation of one of the boilers and its setting are shown in Fig. 5 and the general appearance as set up in the laboratory in Fig. 6.*

The equipment used for testing the boilers provided convenient and accurate means for measuring the coal and water and for making all observations of pressure, temperature, etc., specified in the boiler testing code of the American Society of Mechanical Engineers. It consisted principally of water-weighing tanks, scales, charging cars, sampling cans, apparatus for analyzing flue gases, pressure gages, calorimeters, thermometers and draft gages\*.

---

\* This apparatus is described in detail in "Professional Paper No. 48" United States Geological Survey.






FIG. 5 PLAN AND ELEVATION OF BOILER AND SETTING (PROFESSIONAL PAPER 48, p. 307)




FIG. 6 EXPERIMENTAL BOILER AND TANKS FOR WEIGHING FEED WATER  
(PROF. PAPER 48, p. 304 "B")

The principal dimensions of the boiler and furnace are as follows:—

Length of drum.....	feet.....	21.58
Inside diameter of drum.....	inches .....	42.
Number of tubes, 11 tubes high by 11 tubes wide.....		116
Outside diameter of tubes.....	inches .....	3.5
Width of furnace.....	feet.....	6.16
Length of furnace.....	feet.....	6.58
Mean height of furnace.....	inches .....	26.00
Grate area.....	square feet...	40.55
Ratio of grate area to air space.....		40.17
Water-heating surface in tubes.....	square feet...	1897
Water-heating surface in water legs.....	square feet...	91
Water-heating surface in shell.....	square feet...	43
Total water-heating surface.....	square feet...	2031
Ratio of heating surface to grate area.....		50.1

16. *The Tests.* Since the establishment of the fuel testing division of the United States Geological Survey, more than 500 boiler trials have been made, and of these, 112 involved the use of Illinois coal. Tests were made with each of the 34 samples submitted, the coal being used either in its natural state or in the form of briquets, or both. A number of tests were also made with washed coal.

A summary of the principal observed and derived results of tests with Illinois coals is given in Tables 7 and 8. In these tables only such values as have a direct relation to boiler performance are included; additional data, however, may be found in the reports published by the United States Geological Survey.\*

17. *The description of the coal tested* given in Table 7, Column 1, of this table is the serial number of the test and is useful as a means of identification. The number describing the location from which the sample was taken, is given in Column 2 and the number of the coal bed or seam, in Column 3. The size of the coal is given

\* Bulletin No. 332 and Professional Paper No. 48.

in Columns 4 to 9. The size as shipped (Column 9) was not always the same as that used in the tests since in some cases it was crushed or screened after it was received. The actual size as determined from samples taken during each test is given in precise terms in Columns 5, 6, 7 and 8, and the average diameter calculated from these data is given in Column 9. The proximate analyses (Columns 10 to 14) were made from samples collected for each test and are given in the tables in terms of coal as fired. Calorific values were not determined for every test. The values given (Column 15) were calculated from the proximate analysis and the calorific value determined from the car sample, on the assumption that the B. t. u. per pound of pure coal (ash and moisture free) is the same for each car load shipped to the testing plant.

18. *The performance of the boiler and furnace* is given in Table 8. Column 17 gives the average boiler pressure in pounds per square inch. The standard pressure was 75 but it will be seen that the values given vary from 68 to 81. The draft above the fire (Column 18) was measured in inches of water. In some tests it was as great as .3 inch; the average however, is a little less than .2 inch.

The furnace temperature (Column 19) was observed with a Wanner optical pyrometer. The results given are averages of a number of readings which varied over a considerable range throughout the test. The lowest temperature recorded is 1887° and the highest 2829° F.

The rate of combustion in terms of dry coal fired per hour, per square foot of grate surface (Column 20) is, for most tests, about 25 pounds. This rate, it will be seen, is sufficient to evaporate, in most cases 5½ pounds of water from and at 212° F. per square foot of heating surface per hour (Column 21) or 100 per cent of the rated horse-power (Column 22).

The evaporative efficiency is given in Columns 23, 24 and 25. In Columns 23 and 24 the equivalent evaporation per pound of coal as fired and per pound of dry coal, respectively, is given. The values given in Column 25 represent the over-all efficiency, that is, the ratio of the heat absorbed by the water in the boiler to the potential heat in the coal fed to the furnace. It is evident, therefore, that this is the best measure of the value of any particular fuel for steam generation since it expresses the exact proportion of heat purchased in the form of coal which can be converted into useful energy in the form of steam. Referring to the

TABLE 7 STEAMING TESTS—DESCRIPTION OF COAL

Test No.	U. S. G. S. No.	Coal Bed or Seam	Size of Coal as Shipped	Size of Coal per cent				Average Diameter of Coal, inches	Proximate Analysis of Coal as Fired per cent				Per cent of Sulphur in Coal	Heating value B. t. u. per Pound of Dry Coal
				Over 1 inch	¾ to 1 inch	¼ to ¾ inch	Under ¼ inch		Moisture	Volatile Matter	Fixed Carbon	Ash		
1	2	3	4	5	6	7	8	9	10	11	12	13	14	15
18	1	6	.....	....	60.	40.	....	....	9.64	36.91	38.21	15.19	5.86	11855
19	2	6	.....	....	20.	80.	....	....	10.45	37.77	41.72	10.06	3.75	12569
38	3	7	.....	....	50.	50.	....	....	8.51	31.19	48.75	11.55	1.64	12357
48	4	7	.....	....	90.	10.	....	....	13.47	33.48	41.59	11.45	1.48	12427
50	4	7	.....	....	60.	40.	....	....	12.58	32.44	43.63	11.35	1.55	12459
73	6	5	.....	....	60.	40.	....	....	13.19	32.31	39.62	14.88	4.01	11594
106	6B	5	Run of Mine, washed.....	4.7	19.3	21.5	54.5	.42	15.33	33.76	42.18	8.73	3.12	12762
313	6B	5	Briquets.....	....	....	....	....	....	13.80	31.54	42.86	11.80	3.61	12028
314	6B	5	.....	....	....	....	....	....	13.21	31.96	42.12	2.71	3.70	12101
122	7C	6	Slack.....	....	12.8	18.3	68.9	.30	10.54	31.18	32.98	25.30	4.18	9999
129	7C	6	Slack, washed.....	....	10.5	25.5	64.0	.31	16.45	34.43	40.18	8.94	3.22	12730
142	7D	6	Run of Mine.....	33.5	23.3	15.0	28.2	.82	10.38	34.33	39.08	16.21	4.28	11673
143	7D	6	.....	32.1	22.0	15.6	30.3	.79	10.29	32.34	38.95	18.42	4.66	11212
146	7D	6	.....	24.3	23.3	18.1	34.3	.70	10.29	32.16	38.35	19.20	5.01	11088
516	7E	6	Screened nut.....	4.8	24.7	25.1	45.4	.47	14.47	28.14	35.16	22.23	3.73	10283
101	8	6	Nut.....	58.0	21.9	8.7	11.4	1.12	13.31	34.61	39.39	12.69	5.16	12047
102	8	6	.....	50.4	25.5	10.6	13.5	1.05	12.67	34.23	40.00	13.10	4.68	12002
103	9A	6	Run-of-Mine.....	....	....	....	....	....	12.76	36.12	40.78	10.34	3.94	12506
104	9A	6	.....	....	....	....	....	....	12.21	36.38	40.27	11.14	3.89	12483
105	9A	6	.....	33.3	26.0	15.8	24.9	.83	12.10	36.23	41.05	10.62	4.08	12555
113	9A	6	Run-of-Mine, washed.....	24.6	27.8	20.4	27.2	.74	14.66	36.71	41.19	7.44	3.34	12947
121	9B	6	Lump.....	35.7	29.1	15.0	20.2	.89	10.70	35.84	41.82	11.64	4.11	12438
492	9C	6	Briquets.....	....	....	....	....	....	14.62	32.38	39.13	13.87	3.51	12037
107	10	7	Slack.....	2.9	23.1	26.4	47.6	.44	11.62	30.59	44.93	12.86	1.45	12429
108	10	7	.....	7.6	19.2	21.1	52.1	.45	9.29	31.24	47.84	11.63	1.44	12685
109	10	7	.....	22.8	30.1	17.3	29.8	.73	10.32	30.01	46.27	13.40	1.46	12373
110	10	7	.....	19.2	22.6	18.4	29.8	.70	9.29	32.54	48.11	10.06	1.40	12929
114	10	7	Slack, washed.....	12.8	27.5	23.4	36.3	.60	11.67	32.37	49.87	6.09	1.22	13545
137	11A	7	Screenings.....	21.2	23.6	18.2	37.0	.66	7.84	28.08	51.54	12.54	2.35	12348
138	11A	7	.....	17.4	21.9	15.6	45.0	.59	7.66	29.76	48.65	13.93	2.16	12150
139	11A	7	.....	17.3	19.1	15.8	47.8	.57	7.54	30.09	49.31	13.06	2.57	12254
141	11A	7	.....	20.4	25.3	18.5	35.8	.66	7.65	30.06	50.50	11.79	2.09	12505
111	11B	7	Run-of-Mine.....	39.4	25.2	14.5	20.9	.91	8.17	31.53	48.21	12.09	2.82	12643

FUEL TESTS WITH ILLINOIS COAL

TABLE 7 STEAMING TESTS—DESCRIPTION OF COAL (Continued)

Test No.	U. S. G. S. No.	Coal Bed or Seam	Size of Coal as Shipped	Size of Coal per cent				Average Diameter of Coal, inches	Proximate Analysis of Coal as Fired per cent				Per cent of Sulphur in Coal	Heating Value B. t. u. per Pound of Dry Coal
				Over 1 inch	½ to 1 inch	¼ to ½ inch	Under ¼ inch		Moisture	Volatile Matter	Fixed Carbon	Ash		
1	2	3	4	5	6	7	8	9	10	11	12	13	14	15
112	11B	7	Run-of-Mine.....	28.9	21.3	17.8	32.0	.75	8.93	30.73	48.21	12.13	2.33	12775
115	11B	7	.....	24.6	24.0	18.2	33.2	.71	8.85	28.12	48.08	14.95	2.24	12321
116	11B	7	.....	40.1	21.6	15.2	23.1	.90	7.29	31.34	50.07	11.30	2.50	12933
117	11B	7	Lump.....	33.6	24.8	16.3	25.3	.83	6.69	32.95	47.59	12.77	3.47	12537
118	11B	7	.....	20.4	18.2	17.4	44.0	.61	6.16	33.21	48.91	11.72	3.14	12801
119	11B	7	.....	27.6	24.5	18.3	29.6	.76	6.43	32.23	50.58	10.76	2.22	13079
120	11C	7	¾ to 5-16 in.....	....	16.4	45.8	37.8	.40	9.14	31.03	52.33	7.50	1.64	13370
312	11C	7	Briquets.....	....	....	....	....	....	9.54	31.60	50.92	7.94	1.92	13361
127	12	7	Run-of-Mine.....	30.8	26.5	17.1	25.6	.81	8.49	31.04	45.25	15.22	3.79	11963
128	12	7	.....	46.4	21.2	12.3	20.1	.97	7.93	31.85	46.18	14.04	3.92	12154
131	12	7	.....	23.8	18.1	16.6	41.5	.65	9.54	29.52	43.97	16.97	4.18	11709
133	12	7	.....	25.4	24.3	17.9	31.4	.74	8.79	30.70	44.97	15.61	4.14	11849
135	12	7	Run-of-Mine, washed.....	22.5	28.6	24.1	21.8	.74	10.19	33.30	47.27	9.24	2.58	13104
136	12	7	.....	15.3	22.9	20.8	41.0	.59	10.39	29.39	44.64	15.58	3.56	11867
463	12B	7	Briquets.....	....	....	....	....	....	6.99	32.36	50.24	10.41	2.41	12859
132	13	7	1½ to 6 in.....	31.0	22.6	15.0	31.4	.77	9.95	30.22	47.73	12.10	1.32	12528
134	13	7	.....	23.8	23.8	20.8	31.6	.71	9.64	30.50	48.81	11.05	1.59	12667
144	13	7	½ to 6 in., washed.....	30.0	27.2	19.0	23.8	.81	9.67	32.59	50.18	7.56	1.30	13261
145	13	7	.....	25.2	18.7	20.1	36.0	.69	10.60	31.38	50.84	7.18	1.34	13306
123	14	5	Lump.....	23.3	27.9	19.6	29.2	.72	11.65	34.67	40.12	13.56	4.62	12008
125	14	5	.....	30.4	25.2	17.7	26.7	.79	12.61	33.60	41.30	13.49	4.13	12125
130	14	5	.....	21.4	27.7	25.0	25.9	.72	15.83	33.50	41.38	9.29	3.24	12731
126	15	6	.....	20.5	25.9	21.1	32.5	.68	10.00	33.39	41.20	15.41	4.36	11719
152	15	6	Lump.....	25.5	31.3	21.8	21.4	.78	11.81	37.09	51.04	8.41	3.00	13104
150	16	7	Lump and egg.....	48.1	21.0	12.3	18.6	.99	9.16	29.57	41.73	10.23	1.76	12874
140	18	2	Lump.....	37.3	22.2	15.9	24.6	.86	11.72	37.27	42.00	9.28	4.07	12951
147	18	2	Lump, washed.....	9.5	25.5	26.6	35.4	.55	14.99	37.24	42.14	5.63	2.98	13554
148	18	2	Lump.....	27.1	25.7	17.9	29.3	.75	11.10	37.11	42.00	9.79	3.37	12991
149	18	2	Lump, washed.....	21.7	22.7	28.8	26.8	.70	16.64	36.13	41.51	5.27	2.72	13432
160	19A	7	¾ in. Nut.....	....	21.3	32.0	46.7	.39	12.79	27.24	51.73	8.24	.49	13036
161	19A	7	.....	....	13.6	27.2	59.2	.33	13.43	27.60	50.08	8.89	.50	12911
163	19A	7	.....	....	17.7	34.7	47.6	.38	12.86	28.30	50.80	8.04	.51	13068
170	19A	7	.....	....	13.6	31.3	55.1	.34	13.28	27.72	49.75	9.25	.50	12857

171	19A	7	..	....	13.6	31.8	54.6	.34	13.19	27.56	50.33	8.92	.50	12917
175	19B	7	3 in. Lump.....	60.2	15.7	9.2	14.9	1.10	10.72	29.77	49.30	10.21	.47	13005
204	19B	7	..	44.0	17.2	12.3	26.5	.91	9.56	29.40	51.11	9.93	.61	13050
205	19B	7	..	54.4	15.1	10.7	19.8	1.03	10.30	29.20	50.27	10.23	.55	13001
420	19C	7	Run-of-Mine.....	20.2	24.2	19.1	36.5	.66	8.72	28.41	50.58	12.29	.63	12431
423	19C	7	..	15.8	19.5	18.3	46.4	.57	9.42	28.05	50.72	11.81	.61	12496
424	19D	7	Lump.....	23.9	24.5	18.7	32.9	.71	8.45	29.65	50.24	11.66	.53	12416
425	19D	7	..	37.9	27.4	15.0	19.7	.91	8.51	30.27	49.85	11.37	.51	12460
421	19E	7	1½ in. Nut.....	18.0	45.9	16.6	19.5	.78	9.22	29.28	50.25	11.25	.59	12454
422	19E	7	..	14.4	44.0	17.8	23.8	.72	9.75	28.45	50.67	11.13	.61	15578
292	20	6	Screenings, washed.....	20.1	22.9	18.7	38.3	.64	14.52	31.98	38.01	15.49	4.32	11425
301	20	6	..	17.1	27.7	23.7	31.5	.66	16.51	32.17	40.87	10.45	3.25	12506
302	20	6	..	22.5	28.1	21.9	27.5	.73	16.36	33.54	39.84	10.26	3.22	12548
315	21	6	Lump.....	34.0	21.3	18.1	26.6	.81	14.95	30.33	40.96	13.76	1.60	11945
316	21	6	..	33.6	20.6	16.2	29.6	.80	15.07	30.78	41.90	12.25	1.27	12240
318	21	6	..	....	..	*	*	*	17.31	30.40	42.28	10.01	1.28	12469
324	22A	6	Lump.....	84.6	5.8	3.5	6.1	3.46	11.50	33.44	39.27	15.79	6.24	11484
325	22A	6	..	87.4	5.4	2.6	4.6	3.56	10.53	35.63	40.04	13.80	6.07	11876
328	22A	6	Lump, washed .....	34.1	27.0	22.0	16.9	.87	14.35	36.86	40.57	8.22	3.75	12924
306	23A	6	Lump.....	37.3	19.5	16.2	27.0	.85	14.49	32.37	39.69	13.45	4.62	11759
317	23A	6	Lump, washed .....	18.9	26.7	24.3	30.1	.68	14.64	35.72	40.76	8.88	3.23	12794
321	23B	6	Slack.....	....	+	+	+	+	13.54	36.38	41.67	8.41	3.21	12996
322	23B	6	..	....	+	+	+	+	13.54	36.38	41.67	8.41	3.21	12996
335	24B	6	Lump .....	49.7	19.9	12.4	18.0	1.00	12.14	33.71	42.48	11.67	4.53	12245
336	24B	6	..	22.1	25.2	19.6	33.1	.69	12.60	34.40	43.13	9.87	3.83	12623
337	24B	6	..	92.0	3.2	1.6	3.2	1.88	13.52	32.84	43.17	10.47	3.97	12474
338	25A & B	6	Lump and Run-of-mine.....	61.4	14.3	9.1	15.2	1.99	12.28	35.52	40.53	11.67	3.57	12519
339	25A & B	6	..	82.4	7.2	4.0	6.4	2.17	11.53	34.93	39.75	13.79	4.89	12022
341	26	5	Run-of-mine.....	78.5	8.9	4.4	8.2	2.17	13.55	33.11	40.24	13.10	4.45	12029
342	26	5	..	78.1	9.2	5.8	6.9	2.59	15.68	32.41	39.82	12.09	3.51	12260
353	27	6	..	72.4	11.1	6.8	9.7	2.20	16.00	32.41	37.82	13.77	4.05	11831
354	27	6	..	34.6	25.7	17.6	22.1	.93	15.82	32.50	37.73	13.95	4.80	11713
450	28A	7	Screenings, washed.....	....	..	*	*	....	7.32	30.72	49.84	12.12	1.29	12557
457	28B	7	Screenings.....	....	..	*	*	....	5.81	30.86	52.41	10.92	2.03	12839
448	28C	7	Lump.....	32.3	21.1	13.7	31.9	.79	4.82	30.81	53.82	10.55	1.47	12920
452	28C	7	..	58.4	21.3	9.0	11.3	1.12	7.02	29.93	53.51	9.54	1.18	13070
445	29A	5	Screenings .....	....	..	*	....	....	14.23	34.63	43.96	7.18	2.84	13120
460	29B	5	Run-of-mine.....	34.1	21.5	13.2	31.2	.81	11.09	33.68	41.17	14.06	4.63	11945
461	29B	5	..	51.4	22.4	10.7	15.5	1.04	12.41	35.42	42.15	10.02	3.51	12728
466	29B	5	..	....	..	*	....	....	10.00	36.33	43.01	10.66	3.24	12762
511	30	7	Nut.....	....	..	*	....	....	9.75	39.25	42.69	8.31	3.21	13271
489	31	6	Screenings.....	....	..	*	....	....	14.52	33.74	39.40	12.34	3.36	12303
491	31	6	..	....	..	*	....	....	10.81	33.72	42.74	12.73	3.50	12335
513	33	7	..	....	..	*	....	....	11.50	25.44	42.37	20.69	1.52	11099
509	34B	5	Run-of-mine.....	44.3	22.8	13.4	19.5	1.23	6.56	34.15	51.57	7.72	2.17	13621

\*Briquets. †Briquets broken.

TABLE 8 STEAMING TESTS—PERFORMANCE OF BOILER  
AND FURNACE

Test No.	Boiler Pressure lb. per sq. in.	Draft above Fire inches of Water	Temperature of Furnace Degrees F.	Dry Coal per sq. ft. of Grate Surface Per Hour, pounds	Equivalent Evaporation from and at 212° F. per sq. ft. of Heating Surface Per Hour, pounds	Per Cent of Rated Horsepower Developed	Equivalent Pounds of Water Evap- orated from and at 212° F. Per Pound		Efficiency of Boiler Including the Grate Per Cent	Dry Coal Per Electrical Horsepower Hour, pounds
							Of Coal as Fired	Of Dry Coal		
1	16	17	18	19	20	21	22	23	24	25
18	....	.18	1887	21.00	3.59	100.7	6.51	7.21	58.73	4.85
19	....	.15	....	22.36	3.57	100.1	7.16	8.00	61.47	4.38
38	....	.21	....	21.23	3.41	95.5	7.35	8.04	60.39	4.34
43	....	.16	....	19.84	2.92	81.9	6.38	7.34	57.27	4.73
50	....	.21	....	23.13	3.36	94.2	6.36	7.27	56.36	4.80
73	....	.23	....	22.34	3.30	92.5	6.43	7.40	61.64	4.72
106	.75	.25	2213	25.94	3.39	95.3	5.56	6.56	49.64	5.32
313	.72	.17	....	17.24	2.81	78.7	7.03	8.16	65.51	....
314	.68	.07	2350	21.81	3.42	95.9	5.99	6.91	55.14	....
122	.72	.30	....	20.08	2.19	61.4	5.44	6.08	58.71	5.74
129	.73	.24	....	19.92	3.19	89.6	6.70	8.02	60.81	4.36
142	.81	.16	....	20.07	2.97	83.3	6.65	7.44	61.39	4.70
143	.79	.18	....	18.74	2.69	75.5	6.46	7.20	62.01	4.85
146	.67	.22	....	20.21	2.68	75.2	6.64	7.40	64.45	4.72
516	.79	.13	....	31.99	3.70	103.7	4.95	5.79	54.38	6.03
101	.83.5	.32	....	23.82	3.21	90.1	5.39	6.22	49.86	5.61
102	.78	.25	....	38.36	3.62	101.5	5.58	6.39	51.41	5.46
103	.81	.27	2218	26.53	3.61	101.1	5.94	6.81	52.59	5.13
104	.80	.19	2155	23.22	3.01	84.4	5.70	6.50	50.28	5.37
105	.78	.25	2220	30.26	4.08	114.3	5.93	6.75	51.92	5.17
113	.75	.20	....	25.60	3.05	85.6	5.68	6.66	49.67	5.24
121	.75	.19	....	26.60	3.57	100.0	6.69	7.49	58.15	4.66
492	.76.5	.16	....	22.52	3.50	98.2	6.65	7.79	62.50	4.48
107	.76	.32	2229	21.00	3.20	89.9	6.76	7.65	59.44	4.56
108	.76	.21	....	22.24	3.13	87.6	6.39	7.04	53.60	4.96
109	.78	.29	....	21.46	2.96	83.0	6.90	7.70	60.10	4.53
110	.75	.26	....	20.66	2.48	69.6	6.08	6.71	50.12	5.20
114	.75	.21	....	21.23	3.52	98.7	7.16	8.11	57.82	4.30
137	.74	.16	....	20.98	3.17	88.8	7.76	8.42	64.51	4.14
138	.74	.18	2376	19.94	2.97	83.4	7.68	8.32	66.08	4.20
139	.77	.18	2435	19.70	3.06	85.9	8.02	8.67	68.33	4.03
141	.79	.15	....	18.81	3.11	87.3	7.66	8.29	61.02	4.21
111	.73.5	.28	....	24.35	2.93	82.0	6.15	6.70	51.18	5.21
112	.80	.27	....	22.36	2.90	81.2	6.59	7.23	54.65	4.83
115	.76	.26	....	22.89	3.42	95.9	6.83	7.49	58.71	4.66
116	.76	.22	....	24.19	3.61	101.3	6.94	7.48	55.85	4.67
117	.75.5	.20	....	23.80	3.42	95.8	6.71	7.19	55.38	4.85
118	.77	.16	....	23.16	3.32	93.1	6.74	7.19	54.26	4.85
119	.75	.25	....	25.70	3.75	105.0	6.84	7.31	53.97	4.78
120	.72	.23	....	25.41	3.55	99.5	7.08	7.79	56.27	4.48
312	.71	.11	2400	19.38	3.40	95.4	7.96	8.80	63.60	....
127	.73	.19	....	21.49	3.35	94.0	7.15	7.81	63.04	4.50
128	.75	.19	....	21.45	3.51	98.3	7.54	8.19	65.07	4.26
131	.74	.19	....	20.87	2.91	81.50	7.04	7.74	61.08	4.49
133	.81	.22	....	22.91	3.15	88.2	7.00	7.67	62.51	4.55
135	.74	.18	....	23.09	3.62	101.3	7.86	8.75	64.48	3.99
136	.75	.21	....	20.77	2.91	81.5	7.00	7.81	63.56	4.47
463	.81	.11	2490	18.67	3.20	89.7	7.98	8.58	61.44	4.07
132	.76	.13	....	22.06	3.37	94.5	7.67	8.52	65.67	4.10
134	.78	.18	....	22.55	3.39	95.0	7.58	8.39	63.96	4.16
144	.79	.10	....	20.42	3.70	103.8	8.20	9.08	66.12	3.84
145	.75	.13	....	20.14	3.38	94.7	8.37	9.36	67.93	3.73
123	.73	.28	....	23.60	3.10	87.0	6.49	7.34	59.03	4.76
125	.74	.20	....	20.30	3.08	86.2	6.62	7.58	60.37	4.61
130	.77	.14	....	21.63	3.33	93.3	6.49	7.71	58.48	4.53
126	.69	.18	....	20.44	3.11	87.2	6.86	7.62	62.62	4.58



TABLE 8 STEAMING TESTS—PERFORMANCE OF BOILER  
AND FURNACE (Continued)

Test No.	Boiler Pressure lb. per sq. in.	Draft above Fire inches of Water	Temperature of Furnace Degrees F.	Dry Coal per sq. ft. of Grate Surface per hour, pounds	Equivalent Evaporation from and at 212° F. per sq. ft. of Heating Surface Per Hour, pounds	Per Cent of Rated Horsepower Developed	Equivalent Pounds of Water Evap- orated from and at 212° F. Per Pound		Efficiency of Boiler Including the Grate Per Cent	Dry Coal Per Electrical Horsepower Hour, pounds
							Of Coal as Fired	Of Dry Coal		
1	16	17	18	19	20	21	22	23	24	25
152	75	.13	2439	19.63	3.36	94.3	7.57	8.59	63.30	4.06
150	74	.11	....	19.63	3.56	99.8	8.24	9.08	68.11	3.85
140	75	.18	....	18.51	2.86	80.1	7.60	8.61	64.20	4.06
147	72	.17	....	19.53	3.12	87.4	7.57	8.91	63.48	3.92
148	73	.19	....	18.86	2.99	83.9	7.06	7.94	59.02	4.40
149	74	.14	2060	17.83	3.29	92.2	7.70	9.23	66.36	....
160	77	.14	2428	18.47	3.07	86.1	7.27	8.33	61.71	4.19
161	77	.20	2080	17.77	3.12	87.6	7.62	8.80	65.82	3.97
163	78	.17	2327	20.79	3.57	100.2	7.50	8.61	63.63	4.06
170	79	.16	2039	20.22	3.10	87.0	7.42	8.56	64.29	4.08
171	77	.17	....	20.08	3.23	90.6	7.79	8.97	67.06	3.89
175	74	.09	2470	20.54	3.73	104.7	8.13	9.10	67.50	3.84
204	72.5	.11	2447	20.69	3.50	98.2	8.54	9.45	69.93	3.70
205	71	.12	2448	20.38	3.38	94.9	8.32	9.27	68.86	3.77
420	79.5	.12	....	19.95	3.35	93.9	7.67	8.40	65.26	4.16
423	78.5	.14	....	16.94	2.89	81.0	7.73	8.53	65.02	4.09
424	83.5	.12	....	18.67	3.18	89.1	7.81	8.53	66.35	4.09
425	81	.14	....	19.33	3.32	93.0	7.87	8.61	66.73	4.05
421	82	.11	....	19.46	3.30	92.5	7.70	8.48	65.76	4.12
422	78.5	.12	....	19.46	3.39	95.0	7.88	8.73	67.03	4.00
292	70.5	.10	2020	15.49	2.37	66.3	6.55	7.66	64.75	4.56
301	69	.30	....	24.61	3.54	99.3	6.71	8.04	62.08	4.34
302	76	.17	2708	25.69	3.81	106.7	6.91	8.27	63.65	4.22
315	74.5	.16	2499	20.05	3.27	91.6	6.94	8.16	65.97	4.28
316	69	.15	2401	20.05	3.19	89.3	6.76	7.96	62.80	4.39
318	69.5	.04	2508	25.30	4.11	115.3	6.73	8.14	63.04	4.29
324	71.5	.20	2850	23.08	3.60	100.9	6.91	7.81	65.67	4.47
325	72	.18	2828	22.61	3.60	101.0	7.14	7.97	64.81	4.38
328	71	.14	2829	26.73	4.34	121.8	6.97	8.14	60.82	4.29
306	67	.13	2402	18.50	3.01	84.3	6.97	8.15	66.93	4.29
317	70.5	.13	2397	19.63	3.23	90.4	7.02	8.23	62.12	4.24
321	70.0	.27	....	23.75	3.78	106.0	6.89	7.97	59.22	4.38
322	74.5	.16	....	24.54	3.80	106.6	6.71	7.76	57.66	4.50
335	74.5	.22	2708	20.49	3.30	92.6	7.09	8.07	63.68	4.33
336	73.5	.26	....	21.48	3.29	92.3	6.71	7.67	58.68	4.55
337	72	.20	....	23.63	3.82	107.0	7.00	8.10	62.71	4.31
338	71.5	.21	....	21.36	3.10	87.0	6.38	7.28	56.16	4.80
339	73	.21	....	23.63	3.54	99.1	6.63	7.50	60.25	4.66
341	76	.34	....	20.91	2.84	79.7	6.56	7.58	60.85	4.61
342	77	.30	2264	23.02	3.16	88.6	6.47	7.67	60.42	4.55
353	78	.18	2360	19.83	3.14	88.0	6.66	7.93	64.73	4.40
354	76	.17	2162	19.26	3.08	86.4	6.75	8.02	66.12	4.36
459	80	.15	2601	18.72	3.13	87.7	7.75	8.36	64.29	4.18
457	81	.16	2606	19.85	3.42	95.9	8.13	8.64	64.99	4.04
448	79	.17	2862	22.52	3.88	108.8	8.21	8.63	64.50	4.05
452	82.5	.14	2833	21.97	3.94	110.5	8.35	8.98	66.35	3.89
465	75.5	.15	2065	20.35	3.62	101.5	7.05	8.91	65.58	3.92
460	81.5	.18	2759	21.38	3.44	96.3	7.16	8.05	65.08	4.34
461	80.5	.18	2816	22.32	3.72	104.2	7.31	8.34	63.28	4.19
466	79.5	.16	2784	22.32	3.90	109.2	7.87	8.74	66.14	3.99
511	79.5	.19	....	20.94	3.59	100.7	7.76	8.60	62.58	4.06
489	74	.20	....	21.16	3.49	97.7	7.06	8.25	64.76	4.23
491	82	.24	....	21.65	3.56	100.0	7.35	8.24	64.51	4.24
503	82	.10	2465	26.41	3.23	90.7	5.43	6.13	53.34	5.69
509	82	.22	....	21.50	3.79	106.2	8.24	8.82	62.53	....

values given, it will be seen that but few fall below 55 per cent or above 65 per cent, the maximum and minimum efficiency recorded being 68.11 and 49.64 respectively.

In reviewing the results set forth in Tables 7 and 8 it should be remembered that they apply only to the performance of a hand-fired water-tube boiler of the Heine type and that any conclusions which may be drawn are thus limited. Had it been possible to provide a furnace especially adapted to the burning of each particular coal, the relative efficiency as established by the tests might have been slightly different. The results obtained, however, may be accepted as fairly indicative of the value of the coals tested. With this in view, then, it will be of more than ordinary interest to study the effect of the physical and chemical properties of the fuel upon the performance of the boiler and furnace as set forth in the tables.

19. *Furnace temperature.* It will be seen that while the results do not show any exact relation between efficiency, furnace temperature and rate of combustion, nevertheless they clearly indicate that as the rate of combustion increases, the temperature increases, but that efficiency is only slightly affected by change in combustion-chamber temperature. A comparison with values representing capacity (Column 22) shows that as the combustion chamber temperature increases the capacity is increased.

20. *The evaporative efficiency as affected by moisture in the coal* is not well defined by the results of the tests. While they seem to indicate that coals high in moisture generally give low efficiency it must be remembered that high moisture is often accompanied by high ash content or by poor mechanical structure, either of which properties has a more deleterious effect on efficiency than moisture. That this is true is emphasized by the fact that the heat required to evaporate the water in Illinois coal containing 15 per cent moisture is but little more than 1.5 per cent of its total calorific value.

21. *The effect of sulphur and ash upon evaporative efficiency.* Sulphur is an undesirable element in coal. It generally occurs in combination with iron, as pyrites, and in combination with calcium as gypsum. Of the two sulphur compounds, the former is generally contained in larger quantity in coal and is harmful because it increases the tendency of the coal to clinker. The clinking is especially bad if the percentage of ash is small in proportion to the sulphur. In such coals the pyrites and the ash fuse and form a thin layer of solid clinker, which effectively stops the

passage of air through the grate, thus permitting the grate bars to become heated from the hot fuel bed just above. The heat warps the grate bars and the clinker has such corrosive action on the hot iron that destruction results in a short time. When such clinkering occurs, any attempt to slice the fire fails and only slow and very difficult cleaning of the fires will remove it. Most Illinois coals having a large sulphur content are also high in ash so that the injurious effect of sulphur is not so pronounced as in some other coals. In making the tests it was found that the use of steam served to prevent the clinker from melting into the grate when the ash and sulphur content is large.

Referring to Columns 13, 14, and 25 of Tables 7 and 8 the decrease in efficiency with increasing ash and sulphur will be readily seen. In Fig. 7, which shows this relation graphically, efficiency is plotted against per cent of ash plus sulphur based on dry coal, for all tests run with lump, egg and nut coal. Although many of the plotted points lie at a considerable distance from the average line, its position and direction are rather well defined. It shows that the efficiency drops from 66.5 per cent when the ash plus sulphur is 10 per cent to 55 per cent when ash plus sulphur is 30 per cent. For increases in ash and sulphur beyond 18 per cent the drop in efficiency is relatively rapid.

22. *The effect of size on evaporative efficiency.* The discussion in the preceding paragraph does not take into account the fact that size has much to do with the efficiency with which coal can be burned, and this is one of the chief reasons for the poor alignment of many of the points. The efficiency shown by the same tests together with those made with slack have therefore been plotted against size, expressed in per cent of coal under  $\frac{1}{4}$ -inch in diameter. The resulting relation is shown in Fig 8. Here, too, the points are widely scattered but the slope of the average line is fairly well fixed. Thus a coal giving an efficiency of 66 per cent when 10 per cent of it is under  $\frac{1}{4}$ -inch in diameter, will give an efficiency of only 62 per cent when 60 per cent of it is under  $\frac{1}{4}$ -inch in diameter.




FIG. 7 EVAPORATIVE EFFICIENCY AS AFFECTED BY  
ASH AND SULPHUR




FIG. 8 EVAPORATIVE EFFICIENCY AS AFFECTED BY  
SIZE OF COAL




FIG. 9 COMBINED EFFECT OF SULPHUR PLUS ASH AND SIZE ON EVAPORATIVE EFFICIENCY

Fig. 9 has been drawn to show the combined effect of sulphur plus ash and size, on the evaporative efficiency of Illinois coal. In it lines have been drawn showing the decrease in efficiency with decrease in size for coals having 10, 20 and 30 per cent ash plus sulphur based on dry coal. There are, of course, other factors which affect efficiency but the results of the present tests seem to point to these as the most important. The lines given therefore, may be accepted as defining with considerable accuracy, the performance of Illinois coal when burned in a hand-fired furnace under a water-tube boiler.

23. *Comparative efficiency resulting from the use of washed and unwashed coal.*—It has been shown that the process of washing Illinois coal is effective in reducing the ash and sulphur content. That the evaporative efficiency of the coal thus treated is increased follows directly from the facts just developed. The extent of the

improvement is set forth by Table 9. In this table tests are grouped in the order of the size of coal used. A comparison of the average values given shows that where slack is used washing effects an increase of 4.2 per cent in evaporative efficiency, 2.3 per cent where nut is used, .7 per cent when run-of-mine is used and .6 per cent when lump is used. The extremely small gain for

TABLE 9

## COMPARATIVE EFFICIENCY OF WASHED AND UNWASHED COAL

U. S. G. S. Coal No.	Size	Efficiency	
		Unwashed	Washed
1	2	3	4
1 7C 10	Slack	58.73	61.47
	Slack	58.71	60.84
	Slack	50.12	57.82
Average		55.85	60.04
9A 12	R. o. m.	50.28	49.67
	R o. m.	62.51	64.48
Average		56.40	57.08
13 13	Nut	65.67	67.93
	Nut	63.96	66.12
Average		64.68	67.02
23A 18 18	Lump	66.93	62.12
	Lump	64.20	63.48
	Lump	59.02	66.39
Average		63.38	64.00

the last two sizes named is explained by the fact that, in the process of washing, the coal was crushed to a size under 2 inches, a size which has been shown not to be so well adapted to the kind of grate and furnace used as the larger size.

24. *Comparison of efficiency resulting from the use of raw and briquetted coal.*—Of the 112 boiler tests made, 15 tests were run with briquetted coal. Comparing the results shown in Table 8 with the results of similar tests with raw coal, it will be seen that in most cases where the raw coal is in the form of screenings or

slack, briquetting improves the evaporative efficiency, but where it is in the form of egg, nut or lump, but little difference in performance results. As in the case of coal in its natural state, efficiency decreases as the ash and sulphur content increases. This is shown graphically in Fig. 10. The rather close alignment of the plotted points in this figure is due principally to the uniformity in size of the fuel.




FIG. 10 EVAPORATIVE EFFICIENCY AS AFFECTED BY  
ASH AND SULPHUR IN BRIQUET

25. *The evaporative efficiency of Illinois coal compared with that of coal from other states, as shown by the United States Geological Survey tests, is presented in Table 10. Only tests with bituminous and semi-bituminous coal are here included and the average values given are based only on tests which were made under simi-*

TABLE 10 COMPARATIVE RESULTS OBTAINED FROM COAL  
FROM VARIOUS STATES

State	Kind of Coal	No. of Tests	No. of Coals	Average per cent of Rated Horse-Power Developed	Equivalent Evaporation from and at 212° F., per pound Dry Coal	Efficiency of Combined Boiler and Furnace	B. t. u. per pound of Dry Coal
1	2	3	4	5	6	7	8
Alabama .....	Bituminous .....	10	4	91.9	8.43	64.31	12656
Arkansas .....	Bituminous .....	8	7	89.3	9.03	63.54	13707
Colorado .....	Bituminous .....	1	1	71.9	7.21	55.36	12577
Illinois .....	Bituminous .....	52	25	89.6	7.95	62.66	12349
Iowa .....	Bituminous .....	5	5	90.7	7.13	59.55	11650
Indiana .....	Bituminous .....	24	11	89.5	8.23	63.76	12549
Kansas .....	Bituminous .....	8	6	83.4	8.10	61.26	12780
Kentucky .....	Semi-Bituminous .....	8	3	91.0	9.77	65.41	14417
Kentucky .....	Bituminous .....	3	3	88.9	8.37	62.82	12883
Missouri .....	Bituminous .....	9	7	92.2	7.73	60.18	12246
New Mexico .....	Bituminous .....	6	3	101.3	8.28	64.68	12507
Ohio .....	Bituminous .....	18	9	92.2	8.82	64.88	13130
Pennsylvania .....	Bituminous .....	18	9	89.9	9.75	66.22	14248
Tennessee .....	Bituminous .....	24	9	102.3	8.81	64.18	13261
Virginia .....	Semi-Bituminous .....	10	4	94.2	9.73	65.07	14436
West Virginia .....	Bituminous and Semi-Bituminous .....	36	21	95.5	9.86	65.89	14451



lar conditions of operation. Column 1 gives the name of the state, Column 2 the kind of coal, Column 3 the number of tests included in the average, Column 4 the number of samples of coal, Column 5 the average rate of power developed, Column 6 the efficiency in terms of equivalent evaporation per pound of dry coal, Column 7 the efficiency in per cent and Column 8 the heating value of the coal in B. t. u., per pound of dry coal. The values given in the table show that the average evaporative efficiency of Illinois coal is 62.66 per cent. This compares favorably with the results from any other coal tested and in fact is nearly identical with the general average, 63.1.

### VIII PRODUCER-GAS TESTS

26. *The producer-gas plant* used for the United States Geological Survey tests of Illinois coal consists of two Taylor pressure producers arranged to discharge into a single scrubber, a Westinghouse three-cylinder vertical gas engine rated at 235 horse-power, and a six-pole, 175 kilowatt Westinghouse direct current generator. Auxiliary apparatus was provided for measuring accurately the coal and gas, the steam used by the producer, and all temperatures and pressures necessary for a complete determination of plant efficiency. The general arrangement of the plant is well shown in Fig. 11, and a section through the producer in Fig. 12, (pp. 45, 46).

The principal dimensions of the producer plant are as follows:—

#### Producer

Capacity, horse-power.....	250
Outside diameter.....feet....	7.0
Inside diameter.....feet....	6.5
Height.....feet....	15
Area of fuel-bed.....square feet....	38.5
Diameter of gas delivery pipe.....inches....	22
Type of feed, Bldt automatic continuous feed.	

#### Economizer

Diameter ....feet....	3
Height.....feet....	16.5
Number of 7-inch tubes.....	6

## Scrubber

Diameter.....feet ... 8

Height.....feet.... 20

Material used in scrubber, gas-house coke.

## Tar extractor

Speed, revolutions per minute.....1500

## Purifier

Length of sides.....feet.... 8

Height.....feet.... 3.25

Material used in purifier, oxidized iron filings and wood shavings.

## Gas holder

Diameter.....feet ... 20

Height.....feet.... 13

Capacity.....cubic feet... 4000

27. *The tests* were conducted alternately on the two producers, one being charged while the other was in operation. The schedule adopted involved two sixty-hour runs per week. The first eight or twelve hours of each test were used for bringing the fuel bed to a uniform condition. During this preliminary running, observations were made as in the regular tests, but the record data include only the last 48 or 50 hours, when the running conditions were maintained as uniform as possible. Special attention was directed to the accurate measurements of the coal actually used and charts and checking devices were introduced for this purpose.

Owing to the lack of reliability in the operation of the gas engine, many of the tests made at the beginning of the series were only of a few hours' duration; later, however, no difficulty was experienced in starting the engine and continuing it in operation for a period of 120 hours. During this time two different coals were tested. Altogether 30 tests were made involving the use of 23 different samples of Illinois coal.

28. *Results of the tests.*—The more important observed and calculated results of the tests are given in Table 11. Column 1 of this table is the laboratory number of the test, Column 2 the U. S. G. S. number of the sample tested and Column 3 the size of the coal tested. The proximate analyses of the coal as fired are given in Columns 4 to 8 and the heating value in B. t. u. per pound of dry coal is given in Column 4. The brake horse-power given in Column 10 is the power delivered by the gas engine. Column 11 is the cubic feet of gas delivered by the producer per hour, in terms of standard gas, that is, gas at atmospheric pressure and 60° F. temperature. Column 12 is the calorific value of the gas expressed in B. t. u. per cubic foot of standard gas. Column 13




FIG. 11 SECTION THROUGH GAS PRODUCER (Prof. Paper 48, p. 984)




FIG. 12 ELEVATION SHOWING GENERAL ARRANGEMENT OF  
PRODUCER-GAS PLANT (Prof. Paper 48, p. 983)

TABLE 11 PRODUCER TESTS

Test No.	U. S. G. S. No.	Size of Coal	Proximate Analysis of Coal as Fired, per cent				Sulphur, Per cent (Separately Determined)	B. t. u. per pound of Dry Coal	Brake Horse-Power	Cubic feet of Standard Gas per hour	B. t. u. per cubic foot of Standard Gas	Cubic feet of Standard Gas per pound of Dry Coal	B. t. u. Contained in Gas per pound of Dry Coal Fired	Pounds of Dry Coal Con- sumed per Brake Horse- Power hour
			Moisture	Volatile Matter	Fixed Carbon	Ash								
1	2	3	4	5	6	7	8	9-	10	11	12	13	14	15
6	3	.....	7.62	30.87	51.78	9.73	1.69	13041	235.0	17412	154.8	53.9	8330	1.43
9	4	.....	12.43	32.65	45.70	9.22	1.41	12834	233.0	17881	151.5	58.4	8840	1.37
35	6B	Lump.....	11.47	31.67	40.78	16.08	4.59	11453	243.0	18070	152.0	52.4	7965	1.50
26	7A	Slack.....	12.76	32.35	33.37	21.52	3.82	10721	163.0	17320	109.3	30.6	3350	3.69
27	7B	Nut and pea.....	11.92	33.95	36.67	17.46	4.15	11308	240.2	19580	138.6	48.8	6770	1.75
38	7C	Slack.....	10.08	32.71	38.26	18.95	4.15	11072	205.8	19780	120.2	46.2	5540	2.24
29	8	Nut.....	12.91	33.83	41.67	11.59	4.64	12263	244.8	18610	147.0	55.9	8220	1.43
28	9B	Lump.....	11.99	35.90	40.63	11.48	4.92	12334	244.8	18958	143.7	54.6	7840	1.49
31	10	Slack.....	8.57	32.31	48.45	10.67	1.35	12874	244.2	19580	140.7	68.7	9660	1.24
30	11A	Egg.....	7.08	32.62	49.44	10.86	2.09	12919	247.0	17630	173.4	65.0	11275	1.18
36	11C	No. 5 washed.....	12.78	28.03	47.63	11.56	1.65	12456	204.6	21330	109.8	43.1	4730	2.60
42	11D	No. 3 washed.....	8.67	30.69	53.36	7.28	1.53	13534	236.5	18925	146.1	82.3	12020	1.04
48	11D	.....	7.99	32.08	52.76	7.17	1.56	13554	238.3	.....	154.9	.....	.....	1.02
41	13	Egg.....	8.72	31.07	49.94	10.27	1.66	12798	245.5	18320	156.8	59.2	9280	1.33
37	14	Lump.....	12.68	33.36	41.57	12.39	4.16	12231	234.1	17172	150.6	59.1	8900	1.32
39	15	Lump and egg.....	.....	.....	.....	.....	.....	.....	.....	.....	.....	.....	.....	.....
40	15	.....	9.44	35.48	41.53	13.55	4.06	12107	236.0	19130	142.9	62.3	8900	1.39
43	16	.....	7.68	30.62	51.33	10.37	1.47	12911	236.7	18050	149.5	56.7	8480	1.42
45	18	.....	13.19	35.93	40.84	10.04	4.59	12717	237.3	17814	147.7	63.4	9360	1.26
55	19B	No. 3 Lump.....	9.64	30.68	50.22	9.46	.53	13140	236.7	17430	164.1	69.1	11340	1.13
128	19C	Run-of-mine.....	9.82	29.64	50.34	10.20	.49	12744	166.0	17100	137.8	65.8	9080	1.68
105	21	Lump.....	14.68	30.98	42.93	11.41	1.33	12343	225.5	18170	156.1	57.5	8970	1.47
103	24B	.....	11.48	33.93	43.92	10.71	4.94	12375	236.0	15730	160.5	60.6	9730	1.16
98	23A	No. 5 Lump.....	11.87	36.37	39.87	11.89	4.65	12103	233.3	17780	147.9	56.0	8280	1.43
100	23B	Slack.....	14.77	35.23	40.98	9.02	3.46	12676	213.5	17520	145.0	59.6	8640	1.45
102	22A	Lump.....	11.29	35.60	39.94	13.17	4.88	12100	231.2	17250	159.6	56.1	8950	1.42
104	25	.....	11.35	34.62	40.63	13.40	4.76	12105	236.0	14540	168.0	51.3	8620	1.27
126	26	Run-of-mine.....	13.29	32.02	38.81	15.88	3.52	11547	205.4	17590	147.2	63.1	9290	1.45
127	27	.....	11.35	33.59	41.20	13.86	4.54	11828	147.0	16910	122.5	59.4	7280	2.13
139	29B	.....	12.25	33.76	41.66	12.33	4.42	12250	228.7	.....	141.2	.....	.....	1.39
157	30	Washed.....	5.59	39.30	45.45	9.66	3.37	12910	234.0	15800	154.4	51.6	7980	1.36

is the cubic feet of standard gas per pound of dry coal. Column 14 is the B. t. u. contained in the gas per pound of dry coal fired. This value divided by the heating value of the coal (Column 9) equals the thermal efficiency of the producer. Column 15 is the pounds of dry coal consumed by the producer per brake-horsepower available for outside purposes.

In comparing the results of the producer tests as set forth in Table 11, too much emphasis can not be given the fact that they were subjected to absolutely no refinements. With the exception of three coals one test only has been made on each kind and grade, and the result of each test has, to a great extent, depended upon the ability of the operator to discover the best methods of handling a given coal within the 8 or 10 hours allowed preliminary to the official test. Moreover, all tests were made on one type and in one size of producer, a type designed primarily for anthracite coal, and in carrying out the plan of the tests more effort was made to develop the required power than to observe the proper relation between the gas producing qualities of the coal and the area of the fuel bed.

In spite of all these restrictions it is the opinion of those who were in charge of the tests that certain general relationships have




FIG. 13 CUBIC FEET OF GAS PER POUND OF COAL AS AFFECTED BY PER CENT OF ASH IN DRY COAL

been fairly well established. They may be subject to modification in the light of future investigations, but the conclusions to be drawn from them are sufficiently significant for presentation.

29. *Efficiency as affected by ash in the coal.*—The cubic feet of gas delivered by the producer per pound of coal fired is, perhaps, the most convenient measure of efficiency. Referring to Column 13, Table 11, it will be seen that in general as the ash in the coals increases this quantity decreases. The exact relation for all tests made at full load is shown graphically in Fig. 13. In this figure, cubic feet of standard gas per pound of dry coal is plotted against ash expressed in per cent of dry coal. The average line is drawn so as to include as many of the plotted points as possible. It shows that when the coal contains 8 per cent ash the output of the producer is 67 cubic feet per pound of dry coal fired and that when ash is 20 per cent the output is decreased to 50 cubic feet.

30. *Efficiency as affected by calorific value of the coal.*—The cubic feet of gas per pound of dry coal plotted against B. t. u. per pound of dry coal for all tests made at full load is shown in Fig. 14. Since the heating value of Illinois coal is very nearly inversely proportional to the ash content the relation shown is merely a restatement of the facts brought out in Fig. 13. The points, however, fall in better alignment. It appears from the curve that the output of gas in cubic feet per pound of coal increases from 49 when the calorific value is 11000 B. t. u. per pound of dry coal, to 65 when the calorific value is 13000. Fig. 15 shows the efficiency expressed in per cent plotted against the heating value of the coal. Here the same rise in efficiency is again shown. The average value at 11000 is 58 per cent and at 13000 it is 76 per cent.




FIG. 14 CUBIC FEET OF GAS PER POUND OF COAL, AS AFFECTED BY CALORIFIC VALUE OF THE COAL




FIG. 15 EFFICIENCY OF PRODUCER AS AFFECTED BY CALORIFIC VALUE OF THE COAL



31. *A comparison of Illinois coal with other bituminous coals.* A condensed summary of the more important items relating to Illinois coals compared with those relating to all other bituminous coals tested, is presented in Table 12. The average values given

TABLE 12

A COMPARISON OF ILLINOIS COAL WITH BITUMINOUS COALS  
FROM OTHER STATES FOR GAS PRODUCER SERVICE


	Average of Tests with Ill. Coal	Average of All Tests with Bitum- inous Coal
Composition of fuel, per cent:		
Moisture.....	10.84	6.82
Volatile matter.....	33.06	33.06
Fixed carbon.....	44.06	49.80
Ash.....	12.04	10.32
Sulphur.....	3.15	2.41
B. t. u. per pound of dry coal.....	12000.	13150.
Composition of gas, volume per cent:		
Carbon dioxide.....	9.60	9.84
Oxygen.....	.03	.04
Nitrogen.....	56.81	55.60
Hydrocarbons.....	3.21	3.30
Carbon monoxide.....	18.31	18.28
Hydrogen.....	12.01	12.90
B. t. u. per foot of standard gas.....	146.5	152.1
Cubic feet of standard gas per pound of dry coal.....	59.1	64.7
Pounds of dry coal per brake horse power, hour.....	1.36	1.26

are computed only from tests in which the producer was operated at its rated capacity. It will be noted that while the analysis shows that the Illinois coal contains 4 per cent more moisture and  $2\frac{1}{2}$  per cent more ash the quality of the gas produced is but slightly inferior. Thus the heating value is 146.5 B. t. u. per foot of standard gas when Illinois coal is used and 152.1 when other bituminous coal is used. The output of gas, measured in cubic feet per pound of dry coal, is 59.1 in the one case and 64.7 in the other. Comparing the efficiency at the engine it will be seen that it requires 1.36 pounds of Illinois coal to develop a horse-power and 1.26 pounds when other bituminous coals are used. This comparison is by no means unfavorable and considering the lower selling prices which prevail for Illinois coals the very slight difference in efficiency is almost insignificant.

32. *Relative results of steam and producer-gas tests.*—From theoretical considerations it may easily be shown that it is possible for the gas engine to utilize a much larger amount of the

RELATIVE AMOUNT OF ILLINOIS COAL USED BY STEAM AND  
PRODUCER PLANT

POUNDS PER BRAKE HORSE-POWER HOUR



\*No producer test.

FIG. 16 RELATIVE COAL CONSUMPTION IN GAS AND STEAM PLANTS.

heat supplied than the steam engine. The results of the present tests show how much of this saving is realized in practice.

The ratios of the total coal per brake horse-power hour required by the steam plant and producer gas plant under full load conditions are presented in Fig. 16. The values representing producer plant performance are those of Column 15, Table 11, and those representing steam plant performance are calculated from those of Column 25, Table 8, allowing 85 per cent as the efficiency of the dynamo. It will be seen that the maximum ratio is 3.13 and the minimum 1.50 while the average is 2.61.

## UNITED STATES GEOLOGICAL SURVEY PUBLICATIONS ON FUEL TESTING

The following publications, except those to which a price is affixed, can be obtained free by applying to the Director, Geological Survey, Washington, D. C. The priced publications can be purchased from the Superintendent of Documents, Government Printing Office, Washington, D. C.

*Bulletin No. 261.* Preliminary report on the operations of the coal-testing plant of the United States Geological Survey at the Louisiana Purchase Exposition, in St. Louis, Mo., 1904; E. W. Parker, J. A. Holmes, M. R. Campbell, committee in charge. 1905. 172 pp. 10 cents.

*Professional Paper No. 48.* Report on the operations of the coal-testing plant of the United States Geological Survey at the Louisiana Purchase Exposition, St. Louis, Mo., 1904; E. W. Parker, J. A. Holmes, M. R. Campbell, committee in charge. 1906. In three parts. 1492 pp. 13 pls. \$1.50.

*Bulletin No. 290.* Preliminary report on the operations of the fuel-testing plant of the United States Geological Survey at St. Louis, Mo., 1905, by J. A. Holmes. 1906. 240 pp. 20 cents.

*Bulletin No. 323.* Experimental work conducted in the chemical laboratory of the United States fuel-testing plant at St. Louis, Mo., January 1, 1905, to July 31, 1906, by N. W. Lord. 1907. 49 pp.

*Bulletin No. 325.* A study of four hundred steaming tests, made at the fuel-testing plant, St. Louis, Mo., 1901, 1905, and 1906, by L. P. Breckenridge. 1907. 196 pp.

*Bulletin No. 332.* Report of the United States fuel-testing plant at St. Louis, Mo., January 1, 1906, to June 30, 1907; J. A. Holmes, in charge. 1908. 299 pp.

*Bulletin No. 334.* The burning of coal without smoke in boiler plants: a preliminary report, by D. T. Randall. 1908. 26 pp.

*Bulletin No. 336.* Washing and coking tests of coal and cupola tests of coke, by Richard Moldenke, A. W. Belden, and G. R. Delamater. 1908. 76 pp.

*Bulletin No. 339.* The purchase of coal under Government and commercial specifications on the basis of its heating value, with analyses of coal delivered under Government contracts, by D. T. Randall. 1908. 27 pp.

*Bulletin No. 343.* Binders for coal briquets, by J. E. Mills. 1908. 56 pp.

*Bulletin No. 362.* Mine sampling and chemical analyses of coals tested at the United States fuel-testing plant, Norfolk, Va., in 1907, by J. S. Burrows. 1908. 23 pp.

*Bulletin No. 363.* Comparative tests of run-of-mine and briquetted coal on locomotives, by W. F. M. Goss. 1908. 57 pp.

*Bulletin No. 366.* Tests of coal and briquets as fuel in house-heating boilers, by D. T. Randall. 1908. 44 pp.

*Bulletin No. 368.* Washing and coking tests of coal, by A. W. Belden, G. R. Delamater and J. W. Groves. 1908. 53 pp.

# PUBLICATIONS OF THE ENGINEERING EXPERIMENT STATION

- Bulletin* No. 1. Tests of Reinforced Concrete Beams, by Arthur N. Talbot. 1904. (*Out of print.*)
- Circular* No. 1. High-Speed Tool Steels, by L. P. Breckenridge. 1905. (*Out of print.*)
- Bulletin* No. 2. Tests of High-Speed Tool Steels on Cast Iron, by L. P. Breckenridge and Henry B. Dirks. 1905. (*Out of print.*)
- Circular* No. 2. Drainage of Earth Roads, by Ira O. Baker. 1906. (*Out of print.*)
- Circular* No. 3. Fuel Tests with Illinois Coal. (Compiled from tests made by the Technologic Branch of the U. S. G. S., at the St. Louis, Mo., Fuel Testing Plant, 1904-1907, by L. P. Breckenridge and Paul Diserens. 1909.
- Bulletin* No. 3. The Engineering Experiment Station of the University of Illinois, by L. P. Breckenridge. 1906. (*Out of print.*)
- Bulletin* No. 4. Tests of Reinforced Concrete Beams, Series of 1905, by Arthur N. Talbot. 1906.
- Bulletin* No. 5. Resistance of Tubes to Collapse, by Albert P. Carman. 1906. (*Out of print.*)
- Bulletin* No. 6. Holding Power of Railroad Spikes, by Roy I. Webber. 1906. (*Out of print.*)
- Bulletin* No. 7. Fuel Tests with Illinois Coals, by L. P. Breckenridge, S. W. Parr and Henry B. Dirks. 1906. (*Out of print.*)
- Bulletin* No. 8. Tests of Concrete: I. Shear; II. Bond, by Arthur N. Talbot. 1906. (*Out of print.*)
- Bulletin* No. 9. An Extension of the Dewey Decimal System of Classification Applied to the Engineering Industries, by L. P. Breckenridge and G. A. Goodenough. 1906.
- Bulletin* No. 10. Tests of Concrete and Reinforced Concrete Columns, Series of 1906, by Arthur N. Talbot. 1907. (*Out of print.*)
- Bulletin* No. 11. The Effect of Scale on the Transmission of Heat through Locomotive Boiler Tubes, by Edward C. Schmidt and John M. Snodgrass. 1907. (*Out of print.*)
- Bulletin* No. 12. Tests of Reinforced Concrete T-beams, Series of 1906, by Arthur N. Talbot. 1907. (*Out of print.*)
- Bulletin* No. 13. An Extension of the Dewey Decimal System of Classification Applied to Architecture and Building, by N. Clifford Ricker. 1907.
- Bulletin* No. 14. Tests of Reinforced Concrete Beams, Series of 1906, by Arthur N. Talbot. 1907. (*Out of print.*)
- Bulletin* No. 15. How to Burn Illinois Coal without Smoke, by L. P. Breckenridge. 1908.
- Bulletin* No. 16. A Study of Roof Trusses, by N. Clifford Ricker. 1908.
- Bulletin* No. 17. The Weathering of Coal, by S. W. Parr, N. D. Hamilton, and W. F. Wheeler. 1908. (*Out of print.*)
- Bulletin* No. 18. The Strength of Chain Links, by G. A. Goodenough and L. E. Moore. 1908.
- Bulletin* No. 19. Comparative Tests of Carbon, Metallized Carbon and Tantalum Filament Lamps, by T. H. Amrine. 1908.
- Bulletin* No. 20. Tests of Concrete and Reinforced Concrete Columns, Series of 1907, by Arthur N. Talbot. 1908.
- Bulletin* No. 21. Tests of a Liquid Air Plant, by C. S. Hudson and C. M. Garland. 1908
- Bulletin* No. 22. Tests of Cast-Iron and Reinforced Concrete Culvert Pipe, by Arthur N. Talbot. 1908.
- Bulletin* No. 23. Voids, Settlement and Weight of Crushed Stone, by Ira O. Baker. 1908.
- Bulletin* No. 24. The Modification of Illinois Coal by Low Temperature Distillation, by S. W. Parr and C. K. Francis. 1908.
- Bulletin* No. 25. Lighting Country Homes by Private Electric Plants, by T. H. Amrine. 1908.
- Bulletin* No. 26. High Steam-Pressures in Locomotive Service. A Review of a Report to the Carnegie Institution of Washington. By W. F. M. Goss. 1908.
- Bulletin* No. 27. Tests of Brick Columns and Terra Cotta Block Columns, by Arthur N. Talbot and Duff A. Abrams. 1909.
- Bulletin* No. 28. A Test of Three Large Reinforced Concrete Beams, by Arthur N. Talbot. 1909.
- Bulletin* No. 29. Tests of Reinforced Concrete Beams: Resistance to Web Stresses, by Arthur N. Talbot. 1909.
- Bulletin* No. 30. On the Rate of Formation of Carbon Monoxide in Gas Producers, by J. K. Clement, L. H. Adams, and C. N. Haskins. 1909.
- Bulletin* No. 31. Fuel Tests with House-heating Boilers, by J. M. Snodgrass. 1909.
- Bulletin* No. 32. The Occluded Gases in Coal, by S. W. Parr and Perry Barker. 1909.

# UNIVERSITY OF ILLINOIS

## THE STATE UNIVERSITY

---

### THE UNIVERSITY INCLUDES THE

**COLLEGE OF LITERATURE AND ARTS** (Ancient and Modern Languages and Literatures, Philosophical and Political Science Groups of Studies, Economics, Commerce and Industry).

**COLLEGE OF ENGINEERING** (Unexcelled library; spacious buildings; well-equipped laboratories and shops. Graduate and undergraduate courses in Architecture; Architectural Engineering; Architectural Decoration; Civil Engineering; Municipal and Sanitary Engineering; Electrical Engineering; Mechanical Engineering; Railway Engineering).

**COLLEGE OF SCIENCE** (Astronomy, Botany, Chemistry, Geology, Mathematics, Physics, Physiology, Zoology).

**COLLEGE OF AGRICULTURE** (Animal Husbandry, Agronomy, Dairy Husbandry, Horticulture, Veterinary Science, Household Science).

**COLLEGE OF LAW** (Three years' course).

**COLLEGE OF MEDICINE** (College of Physicians and Surgeons, Chicago). (Four years' course).

**COLLEGE OF DENTISTRY** (Chicago). (Three years' course).

**SCHOOLS—GRADUATE SCHOOL, MUSIC** (Voice, Piano, Violin), **LIBRARY SCIENCE, PHARMACY**, (Chicago), **EDUCATION, RAILWAY ENGINEERING AND ADMINISTRATION.**

**A Summer School** with a session of nine weeks is open each summer.

**A Military Regiment** is organized at the University for instruction in Military Science. Closely connected with the work of the University are students' organizations for educational and social purposes. (Glee and Mandolin Clubs; Literary, Scientific, and Technical Societies and Clubs, Young Men's and Young Women's Christian Associations).

**United States Experiment Station**, State Laboratory of Natural History, Biological Experiment Station on Illinois River, State Water Survey, State Geological Survey.

**Engineering Experiment Station.** A department organized to investigate problems of importance to the engineering and manufacturing interests of the State.

**The Library** contains 122,000 volumes, and 14,000 pamphlets.

**The University offers 526 Free Scholarships.**

For catalogs and information address

**W. L. PILLSBURY, Registrar,**

**Urbana, Illinois.**

**Illinois  
State  
Reformatory  
Print**